

Received: 09/02/2010 Completed: 09/15/2010 Letter: T her P.O.#: Test Report #: 2-84461-0-

Client's Identification Style: Ultravision Window Perf 60/40 UV. Content: PE. Finish: PE. Thickness: 6.3 mil. End Use: Window Film/ Graphics.

Tested For: **Jaime L. Giannantonio** Key Test: NFPA 701-2010 TM#2 Flat 565
 Ultraflex Systems Inc.
 1578 Sussex Tpk., Bldg. #4 Tel: 1-(973)-664-6724 Ext:
 Randolph, NJ 07869 Fax: 1-(973)-627-8506

PC:1H

TEST PERFORMED: NFPA 701 - Standard Methods of Fire Tests for Flame Propagation of Textiles and Films - 2010 Edition - Test Method #2 - Flat Sheet Specimens

SPECIMEN CONFIGURATION: Single Layer; Multi Layer

RESULTS REPORTED: Initially After 72 hours water leaching
 After 3 dry cleanings After 100 hours accelerated weathering
 After 5 launderings @ 160°F

RESULTS:

Length Specimen #	Afterflame (seconds)	Drip Burn (seconds)	Char Length (mm)
1	0	0	7
2	0	0	5
3	0	0	7
4	0	0	6
5	0	0	2
6	0	0	7
7	0	0	3
8	0	0	6
9	0	0	5
10	0	0	7

APPROXIMATE WEIGHT OF MATERIAL (as measured by Govmark): 166 g/m²

FAILURE CRITERIA: For each individual specimen --

Afterflame	Drip Burn	Char Length
Exceeds 2.0 seconds	Exceeds 2.0 seconds	Exceeds 435 mm (17.1")


RETEST PROVISION: Test 5 additional specimens if only 1 specimen fails.

CONCLUSION: Based on the above Results and Failure Criteria, the item tested:

Passes; Fails; Requires testing of 5 additional specimens

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by NFPA 701 - 2010 Edition Test Method #2 Flat Sheet Specimens.

Robert I. Brown



SEP 20 2010
(Page 1 of 2)

AUTHORIZED SIGNATURE
THE GOVMARK ORGANIZATION, INC. / ec/cj

Received:09/02/2010	Completed:09/15/2010	Letter: T	her	P.O.#:	Test Report #:	2-84461-0-
Client's Identification	Style: Ultravision Window Perf 60/40 UV. Content: PE. Finish: PE. Thickness: 6.3 mil. End Use: Window Film/Graphics.					
Tested For: Jaime L. Giannantonio	Ultraflex Systems Inc. 1578 Sussex Tpk., Bldg. #4 Randolph, NJ 07869				Key Test: NFPA 701-2010 TM#2 Flat	565
				Tel: 1-(973)-664-6724	Ext:	
				Fax: 1-(973)-627-8506		

PRECONDITIONING: [] 1 hr @ 220°F (Standard)
 [x] 24 hrs @ 68±9°F (Alternate: Material shrinks/distorts @ 220°F)

REMARKS: 1. Client requested that the restraining clamp binder clips be eliminated to replicate the provisions of the 1996 Test Method #1 version of this document.

2. Adhesive specimens applied to non-combustible board.

CONVERSION FACTORS:
 mm ÷ 25.4 = inches
 g/m² ÷ 28.35 x .835 = oz/yd²

(Page 2 of 2)