

# AVIENT SPECIALTY INKS

## PRODUCT INFORMATION BULLETIN

### 2440 INFINITE FX HD CLEAR 2

Avient™ Specialty Inks INFINITE FX HD CLEAR 2 is a clear developed to create the appearance of glass, gel, water or high gloss surfaces. HD Clear 2 can be used in high density applications or blended with other texture inks to create unique effects. It is also an effective adhesive carrier for foil, flock, and other applications.

#### HIGHLIGHTS

- ▶ High gel, gloss appearance, low-tack feel
- ▶ Use as foil or flock adhesive
- ▶ Use as a High Density Clear, either on its own or tinted with color
- ▶ Use as an overprint clear to enhance color vibrancy and create gloss surfaces
- ▶ Excellent adhesion to fabrics, stretch properties, and wash durability

#### PRINTING TIPS

- ▶ Use consistent, high-tensioned screen mesh and sharp edged squeegees for best print results. Recommended mesh counts can vary depending on particle size
- ▶ For best HD results, use open mesh counts with 200 - 400 micron capillary film and print-flash-print. Use a heavy flood to fully fill the open areas of the stencil with ink then print with medium squeegee pressure
- ▶ Print in last position or flash after each print if using multiple screens
- ▶ Commonly used as a foil or flock adhesive
- ▶ Tintable with plastisol colorants. See Pigment Loading section for suggested tinting percentages. Adjust the % colorant added based on the strength of the colorants and color saturation desired
- ▶ Amber appearance in the bucket but will gain transparency after cure. Achieves good clarity at high ink deposit
- ▶ For flock adhesion, print using 70 duro squeegee 86-110 t/in (34-43 t/cm) with 200 micron stencil and then apply the flock fibers onto the wet ink layer and cure at 320°F (160°C)
- ▶ For improved flock adhesion, add up to 5% INFINITE FX HUGGER CATALYST. Adding Hugger Catalyst reduces pot life to 4-8 hours
- ▶ For foil transfers, print HD Clear 2 using 70 duro squeegee and 86-110 t/in (34-43 t/cm) and 2 strokes. Place foil face up with teflon sheet and apply foil with heat press at 330°F (165°C) for 10-12 sec at medium pressure. Cool shirt before peeling foil. HD Clear 2 can be used as a foil adhesive after cure with a heat press or with an automatic in-line press foil application.

#### COMPLIANCE

- ▶ Non-phthalate
- ▶ For individual compliance certifications and conformity statements, please visit [www.avientspecialtyinks.com/services/compliance-support](http://www.avientspecialtyinks.com/services/compliance-support)

#### PRECAUTIONS

The information above is given in good faith and does not release you from testing inks and fabrics to confirm suitability of substrate and application process to meet your customer standards and specifications



AVIENT  
SPECIALTY  
INKS

V1.01 (Modified: 10/28/2022)



#### RECOMMENDED PARAMETERS



##### Fabric Types

100% cotton, blends, spandex, uncoated nylon, acrylic



##### Mesh

Count: 24-110 t/in (9-43 t/cm)  
Tension: 25-35 n/cm2



##### Squeegee

Durometer: 60/90/60, 60-70  
Profile: Square, Sharp  
Stroke: Hard flood, Slow stroke  
Angle: 10-15%



##### Stencil

2 over 2  
Off Contact: 1/16" (.2cm)  
Emulsion Over Mesh: 15-20% or 200-400 micron



##### Flash & Cure

Flash: 220°F (105°C)  
Cure: 270°F - 320°F (132°C - 160°C)



##### Pigment Loading

upto 10% Wilflex PC  
upto 15% Wilflex EQ  
upto 40% Wilflex RIO / MX  
up to 30% Rutland C3 Boosters



##### Additives

N/A



##### Storage

65-90°F (18-32°C)  
Avoid direct sunlight  
Use within one year of receipt



##### Clean Up

Dispose unused ink responsibly. Standard plastisol cleaners, press wash, or ink degreasant



##### Health & Safety

Find SDS information here:  
[www.avient.com/resources/safety-data-sheets](http://www.avient.com/resources/safety-data-sheets)  
or contact your local CSR

2022, Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the information. Avient makes no warranties or guarantees respecting suitability of either Avient's products or the information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the information and/or use or handling of any product. AVIENT MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the information or products reflected by the information. This literature shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

THIS PRODUCT IS BROUGHT TO YOU BY

**NAZDAR**  
SOURCE ONE

VISIT US ONLINE  
[SourceOne.Nazdar.com](http://SourceOne.Nazdar.com)

CALL US  
888-578-5713

© 2023 Nazdar. All Rights Reserved.  
Specifications subject to change without notice.