



EPIC™ RIO RFU COLORS

WILFLEX™ Epic Rio RFU Colors offer a range of popular industry colors formulated to be vibrant, bold and pure in color. Each color is optimized for unmatched quality and printability in a ready-for-use format. With superior opacity, printers get to color quickly even when using fine mesh screens, saving ink and money. Rio RFU Colors are low cure and designed for wet-on-wet printing and suitable for manual and automatic press.

HIGHLIGHTS

- Popular industry colors, ready for use saving time to mix
- Low cure, save energy
- Opaque colors. Excellent color reproduction over base plate and white, light garments
- Wet-on-wet printing at high production speeds with good resistance to build-up
- Best color fastness
- Matte finish

PRINTING TIPS

- RIO RFU Colors can be cured between 266°F - 320°F (130°C - 160°C)
- Excellent color reproduction using 160-305 t/in (62-120 t/cm) mesh on white, light garments and over a base plate. Use finer mesh and save ink without sacrificing color accuracy.
- For best results on non-woven polypropylene bags, single print using 110-160 t/in (43-62 t/cm) mesh with a 60 or 70 single durometer squeegee
- RIO RFU Colors are not a low-bleed inks; *when printing on fabrics that are prone to bleed underbase with an approved WILFLEX low bleed white and/or blocker
- Exhibits good color retention in high-speed wet-on-wet production with minimal build up. Use fine mesh for best wet-on-wet printing
- Adjust flash cure temperature and dwell time so ink is just dry to touch. Depending on flash unit, a 2 - 3 second flash is adequate
- For cold-peel transfers, use a coated release paper or polyester film. Print colors using 70 duro squeegee and 110-230 t/in (43-91 t/cm) mesh followed by powdering. Gel at 212°F (100°C) for 60 sec. Apply transfer with heat press at 300°F (150°C) for 10-12 sec at medium pressure. For transfers on polyester, back with a low bleed white and/or blocker. Verify process.
- Use ASI K2920 FINESSE to extend the ink for blending colors in halftones or when garment colors allow ink opacity to be decreased. Suitable for use at 270°F (132°C)

COMPLIANCE

- Non-phthalate
- For individual compliance certifications and conformity statements, please visit: www.avient.com/wilflex-compliance

PRECAUTIONS

The information above is given in good faith and does not release you from testing inks and fabrics to confirm suitability of substrate and application process to meet your customer standards and specifications



AVIENT
SPECIALTY
INKS

V3.25 (Modified: 10/27/2022)

PRODUCT INFORMATION BULLETIN



RECOMMENDED PARAMETERS



Fabric Types

100% cotton, 100% polyester*, triblend, polyester blends, cotton/poly blends, cotton/lycra blends, NWPB (non-woven polypropylene bags)



Mesh

Count: 110-305 t/in (43-120 t/cm)
Tension: 25-35 n/cm2



Squeegee

Durometer: 60/90/60, 70/90/70, 60-90
Profile: Square, Sharp
Stroke: Medium flood, Medium-Fast stroke
Angle: 10-15%



Stencil

2 over 2
Off Contact: 1/16" (.2cm)
Emulsion Over Mesh: 15-20%



Flash & Cure

Flash: 220°F (105°C)
Cure: Cotton 140°C/285°F
PES 130°C/266°F (Entire ink film)



Pigment Loading

N/A



Wilflex™ Additives

ASI K2912 VISCOSITY BUSTER LC -1% max
ASI K2920 FINESSE



Storage

65-90°F (18-32°C)
Avoid direct sunlight
Use within one year of receipt



Clean Up

Ink degradant or press wash



Health & Safety

Find SDS information here:
www.avient.com/resources/safety-data-sheets
or contact your local CSR

2022, Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the information. Avient makes no warranties or guarantees respecting suitability of either Avient's products or the information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the information and/or use or handling of any product. AVIENT MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the information or products reflected by the information. This literature shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

THIS PRODUCT IS BROUGHT TO YOU BY

NAZDAR
SOURCEONE

VISIT US ONLINE
SourceOne.Nazdar.com

CALL US
888-578-5713

© 2022 Nazdar. All Rights Reserved.
Specifications subject to change without notice.