



EPIC™ TOP SCORE LC VICTORY COLORS

PRODUCT INFORMATION BULLETIN



WILFLEX™ Epic Top Score LC Victory Colors are low bleed and low cure colors that deliver maximum coverage with the fewest strokes for color consistency when printing directly onto dark fabric or over an under base. With the most popular industry colors, superior on-press performance and exceptional print results on today's garments, printers win big with Wilflex Top Score Victory low cure colors.

RECOMMENDED PARAMETERS

HIGHLIGHTS

- Popular athletic low-bleed standard colors, ready for use saving time to mix
- Opaque colors. Excellent color reproduction over base plate and direct to light and dark garments
- Best color fastness to crocking test
- Low cure, save energy, reduce bleed defects
- Superior bleed resistance, reducing the need to underbase on polyesters
- Matte finish with low surface tack

Fabric Types



100% polyester, polyester blends, 100% nylon Jersey, NWPB (non-woven polypropylene bags)

PRINTING TIPS

- Use consistent, high-tensioned screen mesh and sharp edged squeegees for best print results
- Good color reproduction using 160-230 t/in (62-90 t/cm) on white and dark (blocker) base plates and direct to dark substrates. For lighter ink colors, use 110-160 t/in (43-62 t/cm) for best color reproduction when printing direct to dark substrates. Use a print-flash-print technique when printing direct to dark substrates.
- For best results on non-woven polypropylene bags, single print using 110-160 t/in (43-62 t/cm) mesh with a 60 or 70 single durometer squeegee
- EPIC Top Score LC Victory Colors are low cure and low bleed inks. For challenging fabrics using sublimation dyes, a bleed blocking underbase such as EPIC ARMOR LC may be required
- Adjust flash cure temperature and dwell time so ink is just dry to touch. Depending on flash unit, a 2 - 3 second flash is adequate
- Curing is a time and temperature process, a lower oven temperature setting with a slower belt speed while maintaining recommended ink cure temperature is always best to protect fabric, control dye migration and reduce energy consumption
- EPIC TOP SCORE VICTORY LC Colors can be cured between 270°F - 320°F (132°C - 160°C). Running at the higher end of the temperature range and/or longer dwell times maybe required to achieve proper cure on jobs that contain cotton or heavy weight garments
- For cold peel transfers, use a coated release paper or polyester film. Print colors using 70 duro squeegee and 110-230 t/in (43-91 t/cm) mesh followed by powdering at 212°F (100°C) for 60 sec. Apply transfer with heat press at 300°F (150°C) for 10-12 sec at medium pressure. For transfers on polyester, back with a low bleed white and/or blocker. Verify process.

Mesh



Count: 86-230 t/in (34-90t/cm)
Tension: 25-35 n/cm2

Squeegee



Durometer: 60/90/60, 60-70
Profile: Square, Sharp
Stroke: Hard flood, Slow-Medium stroke
Angle: 10-15%

Stencil



2 over 2
Off Contact: 1/16" (.2cm)
Emulsion Over Mesh: 15-20%

Flash & Cure



Flash: 220°F (105°C)
Cure: 270°F (132°C) Entire ink film

Pigment Loading



N/A

Wilflex™ Additives



ASI Viscosity Buster-1% max

Storage



65-90°F (18-32°C)
Avoid direct sunlight
Use within one year of receipt

Clean Up



Ink degradant or press wash

Health & Safety



AVIENT SPECIALTY INKS

V3.05 (Modified: 08/14/2022)

2022, Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the information. Avient makes no warranties or guarantees respecting suitability of either Avient's products or the information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the information and/or use or handling of any product. AVIENT MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the information or products reflected by the information. This literature shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

THIS PRODUCT IS BROUGHT TO YOU BY



VISIT US ONLINE
SourceOne.Nazdar.com

CALL US
888-578-5713

© 2022 Nazdar. All Rights Reserved.
Specifications subject to change without notice.