




HDB DIGITAL SYSTEM™



RECOMMENDED FABRICS

100% Cotton*
50/50 Cotton/Polyester*
*Primer coat dependent




INK APPLICATION Synthesis Receiver Base™ Parts A and B, once mixed together, should be used from the container without any modifications



ADDITIVES

Do not modify




SCREEN MESH

110-230 t/in (44-90 t/cm)
monofilament



EMULSION

Any direct or indirect emulsion or capillary film in the 35 to 70 micron range



SQUEEGEE

70 Durometer
Sharp edge



CURE TEMPERATURES

320°F (160°C) for up to 3 minutes.
Dependent on dryer speed and temperature settings



CLEAN-UP

Any eco-friendly plastisol screen wash



PRODUCT PACKAGING

Synthesis Receiver Base™: 1 gallon kit
White Primers: quart, gallon, pails
Optium Clear™: quart, gallon, pails



STORAGE OF INK CONTAINERS

65° to 90°F (18° to 32°C)
Avoid storage in direct sunlight
Keep containers well sealed



SDS

Refer to SDS prior to use

FEATURES

The HDB Digital System™ is a 3 part/step easy to print system to be used in conjunction with direct-to-garment digital inks. An HDB primer coat is printed first (for both cotton and low bleed fabrics). Our HDB Synthesis Receiver Base™ (Part A and B) is then printed, followed by our HDB Optimum Clear™.

Synthesis Receiver Base™ is a two-component (Parts A & B) system that must be mixed together before printing can begin. (See important information below).

The HDB Digital System™ is designed for dark and light colored garments. Dark garments require application of the primer; light garments do not require the primer coat.

IMPORTANT MIXING INFORMATION

Synthesis Receiver Base™ Part A and B **must** be mechanically mixed for 5 minutes, making sure that the mixture temperature stays below 95°F (35°C) during the mixing process. After mixing, the combined parts must sit for a minimum of 15 minutes before use. Once mixed, the ink should be covered in the container when not in use. Mixed ink has a working life of 5 days, if stored properly in a closed container. Storage areas should be kept at no higher than 80°F (27°C).

Mixing ratio of Part A to Part B is as follows: 89 grams of Part A to 11 grams of Part B. Mix only the amount needed for the print run. Remember to mechanically mix the two parts together and let the mixed ink sit for at least 15 minutes before use.

IMPORTANT PRINTING INFORMATION

For maximum opacity cotton - 1 print stroke of **HDB White Cotton Primer™**, flash cure to touch, 1 print stroke of mixed **Synthesis Receiver™** ink, then proceed directly to digital printing. **DO NOT FLASH** before digital printing. After the digital print ink has been applied, flash so that it is dry to the touch. Then apply the **Optimum Clear™** over the print and cure.

For maximum opacity 50/50 - 1 print stroke of **HDB White Low Bleed Primer™**, flash cure to touch, 1 print stroke of mixed **Synthesis Receiver™** ink, then proceed directly to digital printing. **DO NOT FLASH** before digital printing. After the digital print ink has been applied, flash so that it is dry to the touch. Then apply the **Optimum Clear™** over the print and cure.

For less opacity on Cotton or Light Colored Cotton - 2 print strokes of the mixed **Synthesis Receiver™** ink, then proceed directly to the digital printing. **DO NOT FLASH Synthesis Receiver Base™** before digital printing. After the digital printing ink has been applied, flash so that it is dry to the touch. Then apply the **Optimum Clear™** over the print and cure.

For maximum wash durability, the ink film should be cured at 320°F (160°C) for 3 minutes, although favorable results might be obtained when curing at 320°F (160°C) for 2.5 minutes. Be sure to test before running production to determine the most optimal curing parameters. Also, follow the digital printer manufacturer's recommendations for curing their inks. We have generally found their recommended cure times to be closer to 2.5 minutes.

Always test for ghosting, dye migration or bleeding on any 100% cotton or 50/50 fabric before beginning production. Test dryer temperatures and wash test printed product before and during a production run. Always wait 24 hours before washing.

LEGAL DISCLAIMER

Recommendations and statements made are based on International Coatings' research and experience. Since International Coatings does not have any control over the conditions of use or storage of the product sold, International Coatings cannot guarantee the results obtained through use of its products. All products are sold and samples given without any representation of warranty, expressed or implied, of fitness for any particular purpose or otherwise, and upon condition that the buyer shall determine the suitability of the product for its own purpose. This applies also where rights of third parties are involved. It does not release the user from the obligation to test the suitability of the product for the intended purpose and application.

REV. 2000005

13929 E. 166th St., Cerritos, CA 90703 • PH (800) 421-6971 or (562) 926-1010 • FAX (562) 926-9486 • E-mail icinfo@iccink.com • www.iccink.com

THIS PRODUCT IS BROUGHT TO YOU BY



VISIT US ONLINE
SourceOne.Nazdar.com

CALL US
888-578-5713

© 2020 Nazdar. All Rights Reserved.
Specifications subject to change without notice.