



Libra™ Matte Mixing Base

RECOMMENDED PARAMETERS

Fabric Types

100% Polyester, Cotton and Poly/
Cotton blended fabrics



Mesh

Count: 80-225t/cm (31-88t/cm)
Tension: 18-35n/cm3



Squeegee

70 or 60-90-60
Profile: sharp, square
Stroke: x2 stroke, medium speed
Angle: 10-15%



Stencil

Standard Emulsion
Off Contact: 1/16" (2mm)
Emulsion Over Mesh: 25-40 micron



Flash & Cure

Flash: 300°F(149°C) for 4 seconds (on
preheated pallets)
Cure: 60 seconds at 270°F(132°C)



Pigment Loading

Libra™ Silicone Pigments Maximum
20%



Libra™ Additives

Libra™ Catalyst: 3-5%
Libra™ Retardant: 0.5-3%



Storage

Store in sealed containers 12 months
from manufacture >40°F (5°C)
<77°F(25°C)



Clean Up

Standard plastisol cleaners



Health & Safety

Find SDS information here:
[www.avient.com/resources/safety-
data-sheets](http://www.avient.com/resources/safety-data-sheets) or contact your local CSR



Libra™ Matte Mixing Base (LIB0207) is a medium viscosity opaque base with excellent printability to bring a matte effect to your silicone prints. The ink is used with Libra™ pigments and toners for a matte effect with extreme stretchability while maintaining a super-soft flexible hand.

HIGHLIGHTS

- Matte finish
- Non-tacky hand
- Excellent coverage and opacity
- Super-soft hand feel
- Extreme stretchability

PRINTING TIPS

- Use 3-5 parts Libra™ Catalyst and 0.5-3 parts Libra™ Retardant. Libra™ pigments or toners can be added up to 20 parts. Mix well and print. To prevent wastage only catalyze what is needed to print for 4 hours.
- Colors should be made in accordance with Libra™ IMS3.0 Pantone® mixing system with a maximum of 20% pigment loading.
- Use 80-225t/cm (31-88t/cm) mesh screens for best performance.
- Print with 1/16" or 2mm off contact.
- Print two strokes to ensure the mesh is clear and you have a good ink deposit.
- Flash between prints.
- Clean the stencil area when stopped to prevent screen blockages.
- Prints should be cured at 270°F /132°C for 60 seconds. Check the cure temp at the ink surface.
- Test all prints for print durability before starting the production run.

COMPLIANCE

- Non-PVC, non-phthalate
- Visit www.avient.com/products/screen-printing-inks/zodiac-libra for more information

PRECAUTIONS

- The information above is given in good faith and does not release you from testing inks and fabrics to confirm suitability of substrate and application process to meet your customer standards and specifications

AVIENT
SPECIALTY
INKS

V3.00 (Modified: 02/17/2021)

2021, Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the information. Avient makes no warranties or guarantees respecting suitability of either Avient's products or the information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the information and/or use or handling of any product. AVIENT MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the information or products reflected by the information. This literature shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.