



PERFORMANCE GUIDE

www.Mactac.com

Version #2 (0515)

Approved by J. S.

**PRODUCT: PGD6000 Series Gloss
Dry Erase Laminate**

PERMACOLOR®

The **Permacolor** system is a series of pressure sensitive products for mounting and overlaminating in the imaging industries. Pressure sensitive **Permacolor** provides fast, efficient processing through cold roll lamination techniques without the need for heat, drying or messy coating operations.

PRODUCT DESCRIPTION

The **overlaminating films** is a family of pressure sensitive adhesive coated, clear overlaminating films that are available in a variety of surface finishes. These films are designed for use over digital images (ink jet, electrostatic, and thermal) to impart protection from abrasion, moisture, and other potentially damaging effects in both indoor and outdoor environment.

PGD6000 is an economical, gloss clear 1-mil **polyester** film top-coated on one side for perfect dry-erase capabilities and on the other with a permanent clear acrylic pressure sensitive adhesive, recommended for indoor and outdoor use. The adhesive is protected by a 78# white Kraft release liner that provides for easy liner removal and a smooth adhesive surface.

PHYSICAL PROPERTIES	TYPICAL VALUES*	TEST METHOD
Thickness , inches ()		ASTM-D645
Film plus adhesive	0.0020 (51)	
Total product	0.0032 (81)	
Quick Tack , lb./in. (N/25 mm)		Mactac CTM-25
Stainless Steel	1.5 (6.7)	
Peel Adhesion , lb./in. (N/25 mm)		PSTC - 1
Stainless Steel - 15 minutes	1.9 (8.2)	
- 24 hr.	2.5 (11)	
Temperature Range Guidelines		
Application:	Above 40°F (5°C) for best results.	
End Use:	-40° to 180°F (-40° to 82°C)	

DURABILITY:

This product has up to one (1) year outdoor use. While all Permacolor overlaminating films have UV resistance built in to help extend the life of your image, the durability of the image is mainly dependent upon the quality of the inks (see technical data sheets given by the ink manufacturers) and pressure sensitive media being used.

SHELF LIFE

Two years when stored at 75°F (24°C) and 50% relative humidity or less. Note: Mactac recommends that rolls be stored on end or suspended from the core.

GENERAL COMMENTS

- Where exposure to moisture, chemicals, solvents or high pressure wash is anticipated, Mactac recommends sealing the edges with varnish, silicone or other sealant to prevent penetration by these liquids.
- Overlaminates should not be applied onto dusty or dirty prints.
- Mactac's pressure sensitive mounting films are intended for "Cold Roll Lamination" (40°F - 104°F). The addition of heat while simultaneous mounting with Thermal Overlaminates may result in curl or have other detrimental effects on the finished product.
- Whenever possible, always test first to ensure end-use capability.

RECOMMENDED DRY ERASE MARKERS: (highlighted markers tested best)

EXPO Low Odor	Crayola Dry Erase Crayon	Universal 43651
SRX Board Dudes	Bic Low Odor	EXPO 2
Wipe-Off	Quartet-Enduraglide	Liquid Mark low odor 2400
TUL OMO4112	Marks-A-Lot (Avery)	EXPO Washable
Office Max	Staples Remarx	EXPO Vis-à- Vis Wet Erase

Please note: All markers worked very well for the first 48 hours. However, just like you see on dry-erase white boards the longer the marker is on the film, the harder it is to wipe them off. Over time some ghosting, especially with the specific colors like red, is to be expected. This can be cleaned with dry erase board cleaner. Do not use detergents or spray cleaners like Fantastic® or Windex® to clean dry-erase surfaces.

Highlighted markers still wiped of easily after 3 weeks. High solvent markers like the original EXPO may need the help of the EXPO Dry-Erase board cleaner to remove after one week.

Not all dry-erase pens are equal; therefore, the user is responsible for testing specific dry erase markers, which may or may not be on this list, for suitability.

- 1) The user is responsible for determining the product's suitability, including adhesion and if needed, removal characteristics when used in applications other than listed specifically in this Performance Guide.**
- 2) If there are any questions about applications, please contact your Mactac sales representative to discuss your requirements for recommendations.**
- 3) If this is a printed Performance Guide it is an uncontrolled document. Please check the Mactac website for the latest, most up-to-date version.**

** Values given are typical for unprocessed product and are not for use as specifications. Processing may change the values.*

CALL 1-800-321-8834 for additional product information

IMPORTANT NOTICE: The information given and recommendations made herein are based on our research and are believed to be accurate. In every case, user shall determine before using any product in full scale production, whether such product is suitable for their particular purpose under their own operating conditions. The products discussed herein are sold without any warranty as to merchantability, expressed or implied. User assumes all risk and liability whatsoever in connection with their use of any product. When used as recommended in this Performance Guide, some types of graphics and end uses may be warranted by the Mactac Open Image Warranty™. Contact Mactac for specific warranty information. Ultimately, sellers and manufacturers only obligation shall be to replace or credit such quantity of the product proved to be defective at its discretion.

™ Trademark of Morgan Adhesives Company LLC

® Registered Trademark of Morgan Adhesives Company LLC
www.Mactac.com



THIS PRODUCT IS BROUGHT TO YOU BY

NAZDAR
SOURCEONE

VISIT US ONLINE
SourceOne.Nazdar.com

CALL US
888-578-5713

© 2022 Nazdar. All Rights Reserved.
Specifications subject to change without notice.