



MagnaPrint® Crosslinker 500

MagnaPrint® Crosslinker 500 is used to reduce the curing time or temperature of printing pastes.

MagnaPrint Crosslinker 500 is particularly useful where dryers have insufficient dwell time or when printing temperature sensitive fabrics such as nylon.

Application

MagnaPrint Crosslinker 500 can be used at varying concentrations up to a maximum of 3%. Trials should be carried under specific printing conditions to arrive at the correct addition level.

Once added to a print paste, **MagnaPrint Crosslinker 500** will remain active for a maximum of 7 days.

Minimum curing recommendation - 2 minutes at 120°C (248°F)

SPECIFICATION



CURE TEMPERATURE

2 minutes at 120°C (248°F)



STORAGE

In cool place properly closed:
>5°C (40°F) <25°C (77°F)



HEALTH & SAFETY

MSDS available upon request



CLEAN UP

Wash off screen using water and mild detergent

All information is given in good faith but without warranty. They do not release you from testing our products as to their suitability for the intended processes and uses.



MagnaColours® Limited

Upper Cliffe Road,
Dodworth Business Park,
Barnsley, S75 3SP, UK

T: 00 44 (0) 1226 731751

F: 00 44 (0) 1226 731752

E: info@magnacolours.com

www.magnacolours.com

Company registered in

England No. 01378495.

VAT No. GB 997 3172 70