



## MagnaPrint® Pearl Flex Neutral

### Ready to print pearlescent stretchy pastes

MagnaPrint® Pearl Flex Neutral is a ready to use stretchy / flexible print paste containing speciality pigments to obtain a “metallic-like” effect.

MagnaPrint® Pearl Flex Neutral has excellent elasticity properties and can be printed directly onto the fabric to achieve fantastic stretch and durability without the need for an under base

MagnaPrint® Pearl Flex Neutral can be pigmented with the addition of up to 6% Eco Pigments to give desired shade.

### Application

MagnaPrint® Pearl Flex Neutral should be printed through a 32-61 (86 -156) mesh screens with rectangular profile squeegees.

As the particle size is 10-60 micron this should be considered when selecting screen mesh.

When printing as part of a multicoloured design print the MagnaPrint® Pearl Flex Neutral as the last screen to avoid pick up.

After printing the garment/panel should be cured, ideally for 2 - 2½ minutes at 165°C (330°F).

All information is given in good faith but without warranty. They do not release you from testing our products as to their suitability for the intended processes and uses.

### SPECIFICATION



#### FABRIC TYPES

Cotton / Poly Cotton blends



#### MESH

32 - 61T (86 - 156)



#### SQUEEGEE

Medium 65° Shore  
Rectangular



#### STENCIL

Water resistant emulsion



#### CURE TEMPERATURE

2 - 2½ minutes at 165°C  
(330°F)



#### PIGMENT LOADING

Up to 6% MagnaPrint®  
Eco Pigments



#### ADDITIVES

Retardant Gel Conc, Crosslinker  
100, Softener TS Conc



#### STORAGE

In cool place properly closed:  
>5°C (40F) <25°C (77F)



#### HEALTH & SAFETY

MSDS available upon  
request



#### CLEAN UP

Wash off screen using water  
and mild detergent



**MagnaColours® Limited**  
Upper Cliffe Road,  
Dodworth Business Park,  
Barnsley, S75 3SP, UK

T: 00 44 (0) 1226 731751  
F: 00 44 (0) 1226 731752  
E: info@magnacolours.com  
www.magnacolours.com

Company registered in  
England No. 01378495,  
VAT No. GB 997 3172 70