

11655W1W WILFLEX ONE LB WHITE

Wilflex™ One LB White is a non-PVC, non-phthalate premium plastisol white ink for applications on cotton/polyester blends where moderate bleed resistance is required. The Low Bleed White can also be used over Wilflex One Underbase Gray on performance polyester and difficult dye migration fabrics. Wilflex One LB White has excellent opacity and optical brightness to give a premium look.



Highlights

- ▶ Non-PVC, Non-phthalate
- ▶ Excellent bleed resistance
- ▶ Optically bright
- ▶ High opacity
- ▶ Matte finish
- ▶ Smooth surface
- ▶ Excellent stretch
- ▶ Print through fine meshes
- ▶ Use as a first-down underbase flash white or as a hi-light white



Printing Tips

- ▶ For best results, Print - Flash - Print followed by color
- ▶ Alternate process, Print - Flash followed by color
- ▶ Allow ink to cool prior to printing subsequent layers
- ▶ Use consistent, high-tensioned screen mesh to optimize performance properties



Compliance

- ▶ Non-PVC, Non-phthalate
- ▶ Passes major brand restricted substance list (RSL) and manufacture restricted substance list (MRSL) requirements
- ▶ For individual compliance certifications, please visit www.wilflex.com/compliance



Precautions


- ▶ Do not dry clean, bleach or iron printed area
- ▶ Stir plastisols before printing
- ▶ Avoid over flashing as it can result in poor intercoat adhesion of colors.
- ▶ Perform fusion tests before production. Failure to cure ink properly may result in poor wash fastness, inferior adhesion and unacceptable durability. Ink flash and cure temperatures should be measured using a thermoprobe placed directly in the wet ink film and verified on the production run substrate(s) and production equipment. It is the responsibility of the printer to determine that the correct ink has been selected for a specific substrate and the application processes meet your customer's standards or specifications.
- ▶ Adjust the time and temperature settings for the flash station and dryer to reach minimal flash and full cure temperatures respectively.
- ▶ Wilflex products have been carefully designed to perform within a given viscosity range and any dramatic change in viscosity may result in a change in printing characteristics..
- ▶ Some fabric dyes may cause ghosting effect if not properly tested.
- ▶ **AVOID CONTAMINATION OF NON-PVC INKS:** Do not add or mix other inks, additives or extenders with Wilflex One inks. All buckets, palette knives, stirring apparatus, squeegees, flood bars and screens must be cleaned properly and free of phthalates and pvc-containing inks. Non-phthalate emulsions and pallet adhesives must be used. Failure to follow these precautions may cause phthalate or PVC contamination in violation of consumer protection laws, regulations or brand specifications
- ▶ Any application not referred in this product information bulletin should be pre-tested or consultation sought with Wilflex Technical Services Department prior to printing
- ▶ Email: techserviceswilflex@polyone.com

Recommended Parameters



Fabric Types

100% polyester, cotton/polyester blends




Mesh

Counts: First down white:
86 - 156 t/in (34 - 61 t/cm)
Smoothing white and/or Hi-Light white:
230 - 305 t/in (90 - 120 t/cm)
Tension: 25-45 n/cm²



Squeegee

Durometer: 60-90, 70/90, 70/90/70
Edge: Sharp
Stroke: Hard flood, fast stroke
**Do not use excess squeegee pressure.*



Non-Phthalate Stencil

Direct: 2 over 2
Capillary/Thick Film: N/A
Off Contact: 1/16" (.2cm)



Flash & Cure Temperatures

Flash: 220°F (105°C) for 3 - 5 seconds
Cure: 300°F (149°C)



Additives

Reducer: Wilflex One Viscosity Buster
- 1% max
**All percentages listed at % by weight.*



Shipping & Storage

65°F - 90°F (18°C - 32°C)
Avoid direct sunlight
Use within one year of receipt



Clean Up

Ink degradant or press wash



Health & Safety

SDS: www.polyone.com or
Contact your local CSR.