



Received: 12/15/2000	Completed: 12/19/2000	Letter: A	rb	P.O.#:	Test Report #:	2-32322-0-
Client's identification	Jetflex					
Tested For: Brian Lynch Ultraflex Systems Inc. 365 Franklin Avenue Rockaway, NJ 07866				Key Test: NFPA 701-96 TM#2 Flat MEA 275 Tel: 1-(973)-627-8608 Ext: Fax: 1-(973)-627-7022		

Test Category: NFPA 701-96 TM2 Specifier: NYC Flex Signs CODE: 275-375-1675

TEST PERFORMED: NFPA 701 - Standard Methods of Fire Tests for Flame Resistant Textiles and Films 1996 Edition - Test Method #2 - Flat Sheet Specimens
as cited by The City of New York Department of Buildings Technical Policy and Procedure Notice #11/99 - Safety Standards for the Erection of Flex Sign Structures

SPECIMEN CONFIGURATION: ☒ Single Layer; ☐ Multi Layer

TESTED: ☒ Initially
☐ After 72 hours water leaching
☐ After 100 hours accelerated weathering

RESULTS: Specimen #	Afterflame (seconds)	Drip Burn (seconds)	Char Length (mm)
1	0.0	0.0	325
2	0.0	0.0	305
3	0.0	0.0	330
4	0.0	0.0	312
5	0.0	0.0	325
6	0.0	0.0	295
7	0.0	0.0	300
8	0.0	0.0	288
9	0.0	0.0	288
10	0.0	0.0	350

APPROXIMATE WEIGHT OF MATERIAL (as measured by Govmark): 452 g/m²

FAILURE CRITERIA: For each individual specimen --

Afterflame	Drip Burn	Char Length
Exceeds 2.0 seconds	Exceeds 2.0 seconds	Exceeds 435 mm (17.1")

RETEST PROVISION: Test 5 additional specimens if only 1 specimen fails.

CONCLUSION: Based on the above Results and Failure Criteria, the item tested:

☒ Passes; ☐ Fails; ☐ Requires testing of 5 additional specimens


(continued on page 2)

Received: 12/15/2000	Completed: 12/19/2000	Letter: A	rb	P.O.#:	Test Report #:	2-32322-0-
Client's Identification	Jetflex					
Tested For: Brian Lynch Ultraflex Systems Inc. 365 Franklin Avenue Rockaway, NJ 07866				Key Test: NFPA 701-96 TM#2 Flat MEA 275 Tel: 1-(973)-627-8608 Ext: Fax: 1-(973)-627-7022		

CONVERSION FACTORS: mm ÷ 25.4 = inches
 g/m² ÷ 28.35 x .835 = oz/yd²

REMARKS: .
None.

CERTIFICATION:
I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by NFPA 701 - 1996 Edition Test Method #2 Flat Sheet Specimens.



AUTHORIZED SIGNATURE 7-6-05
THE GOVMARK ORGANIZATION, INC.
dd

Received: 12/15/2000	Completed: 12/26/2000	Letter: A1	rb	P.O.#:	Test Report #: 2-32322-1-
Client's Identification	Jetflex				
Tested For: Brian Lynch Ultraflex Systems Inc. 365 Franklin Avenue Rockaway, NJ 07866			Key Test: NFPA 701-96 TM#2 Flat MEA WL 375 Tel: 1-(973)-627-8608 Ext: Fax: 1-(973)-627-7022		

Test Category: NFPA 701-96 TM2 Specifier: NYC Flex Signs CODE: 275-375-1675

TEST PERFORMED: NFPA 701 - Standard Methods of Fire Tests for Flame Resistant Textiles and Films 1996 Edition - Test Method #2 - Flat Sheet Specimens
as cited by The City of New York Department of Buildings Technical Policy and Procedure Notice #11/99 - Safety Standards for the Erection of Flex Sign Structures

SPECIMEN CONFIGURATION: ☒ Single Layer; ☐ Multi Layer

TESTED: ☐ Initially
☒ After 72 hours water leaching
☐ After 100 hours accelerated weathering

RESULTS: Specimen #	Afterflame (seconds)	Drip Burn (seconds)	Char Length (mm)
-----	-----	-----	-----
1	0.0	0.0	250
2	0.0	0.0	230
3	0.0	0.0	230
4	0.0	0.0	200
5	0.0	0.0	225
6	0.0	0.0	240
7	0.0	0.0	210
8	0.0	0.0	200
9	0.0	0.0	210
10	0.0	0.0	225

APPROXIMATE WEIGHT OF MATERIAL (as measured by Govmark): 452 g/m²

FAILURE CRITERIA: For each individual specimen --

Afterflame	Drip Burn	Char Length
-----	-----	-----
Exceeds 2.0 seconds	Exceeds 2.0 seconds	Exceeds 435 mm (17.1")

RETEST PROVISION: Test 5 additional specimens if only 1 specimen fails.

CONCLUSION: Based on the above Results and Failure Criteria, the item tested:

☒ Passes; ☐ Fails; ☐ Requires testing of 5 additional specimens

(continued on page 2)



The
Govmark
Organization, Inc.

96-D Allen Boulevard
Farmingdale, New York 11735-5626 USA
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956
e-mail: info@govmark.com

Page 2

Received: 12/15/2000	Completed: 12/26/2000	Letter: A1	rb	P.O.#:	Test Report #:	2-32322-1-
Client's Identification	Jetflex					
Tested For: Brian Lynch Ultraflex Systems Inc. 365 Franklin Avenue Rockaway, NJ 07866				Key Test: NFPA 701-96 TM#2 Flat MEA WL 375 Tel: 1-(973)-627-8608 Ext: Fax: 1-(973)-627-7022		

CONVERSION FACTORS: $\text{mm} \div 25.4 = \text{inches}$
 $\text{g/m}^2 \div 28.35 \times .835 = \text{oz/yd}^2$

REMARKS:
None.

CERTIFICATION:
I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by NFPA 701 - 1996 Edition Test Method #2 Flat Sheet Specimens.

Jean D'Amore

AUTHORIZED SIGNATURE 7-6-05
THE GOVMARK ORGANIZATION, INC.
dd



The
Govmark
Organization, Inc.

96-D Allen Boulevard
Farmingdale, New York 11735-5626 USA
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956
e-mail: info@govmark.com

Page 1

Received: 12/15/2000	Completed: 01/03/2001	Letter: A2	rb	P.O.#:	Test Report #: 2-32322-2-
Client's Identification	Jetflex				
Tested For: Brian Lynch Ultraflex Systems Inc. 365 Franklin Avenue Rockaway, NJ 07866			Key Test: NFPA 701-96 TM#2 Flat MEA AW 1675 Tel: 1-(973)-627-8608 Ext: Fax: 1-(973)-627-7022		

Test Category: NFPA 701-96 TM2 Specifier: NYC Flex Signs CODE: 275-375-1675

TEST PERFORMED: NFPA 701 - Standard Methods of Fire Tests for Flame Resistant Textiles and Films 1996 Edition - Test Method #2 - Flat Sheet Specimens
as cited by The City of New York Department of Buildings Technical Policy and Procedure Notice #11/99 - Safety Standards for the Erection of Flex Sign Structures

SPECIMEN CONFIGURATION: ☒ Single Layer; ☐ Multi Layer

TESTED: ☐ Initially
☐ After 72 hours water leaching
☒ After 100 hours accelerated weathering

RESULTS: Specimen #	Afterflame (seconds)	Drip Burn (seconds)	Char Length (mm)
1	0.0	0.0	190
2	0.0	0.0	240
3	0.0	0.0	220
4	0.0	1.0	210
5	0.0	0.0	155
6	0.0	0.0	220
7	0.0	0.0	230
8	0.0	0.0	190
9	0.0	0.0	190
10	0.0	0.0	240

APPROXIMATE WEIGHT OF MATERIAL (as measured by Govmark): 452 g/m²

FAILURE CRITERIA: For each individual specimen --

Afterflame	Drip Burn	Char Length
Exceeds 2.0 seconds	Exceeds 2.0 seconds	Exceeds 435 mm (17.1")

RETEST PROVISION: Test 5 additional specimens if only 1 specimen fails.

CONCLUSION: Based on the above Results and Failure Criteria, the item tested:

☒ Passes; ☐ Fails; ☐ Requires testing of 5 additional specimens

(continued on page 2)


Received: 12/15/2000	Completed: 01/03/2001	Letter: A2	rb	P.O.#:	Test Report #:	2-32322-2-
Client's identification	Jetflex					
Tested For: Brian Lynch Ultraflex Systems Inc. 365 Franklin Avenue Rockaway, NJ 07866				Key Test: NFPA 701-96 TM#2 Flat MEA AW 1675 Tel: 1-(973)-627-8608 Ext: Fax: 1-(973)-627-7022		

CONVERSION FACTORS: $\text{mm} \div 25.4 = \text{inches}$
 $\text{g/m}^2 \div 28.35 \times .835 = \text{oz/yd}^2$

REMARKS: .
None.

CERTIFICATION:

I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by NFPA 701 - 1996 Edition Test Method #2 Flat Sheet Specimens.



AUTHORIZED SIGNATURE 7-6-05
THE GOVMARK ORGANIZATION, INC.
id