



Received:09/02/2010	Completed:09/08/2010	Letter: S	her	P.O.#:	Test Report #:	2-84460-0-
Client's Identification	Style: Jetflex/ Normandy Pro. Content: Polyester. Finish: PVC. Weight:13 oz/yd ² . End Use: Sign, Banner & Billboard Media.					
Tested For: Jaime L. Giannantonio Ultraflex Systems Inc. 1578 Sussex Tpk., Bldg. #4 Randolph, NJ 07869				Key Test: NFPA 701-2010 TM#2 Flat		340
				Tel: 1-(973)-664-6724		Ext:
				Fax: 1-(973)-627-8506		

PC:1H

TEST PERFORMED: NFPA 701 - Standard Methods of Fire Tests for Flame Propagation of Textiles and Films
- 2010 Edition - Test Method #2 - Flat Sheet Specimens

SPECIMEN CONFIGURATION: ☒ Single Layer; ☐ Multi Layer

RESULTS REPORTED: ☒ Initially ☐ After 72 hours water leaching
☐ After 3 dry cleanings ☐ After 100 hours accelerated weathering
☐ After 5 launderings @ 160°F

RESULTS:

Length Specimen #	Afterflame (seconds)	Drip Burn (seconds)	Char Length (mm)
1	0	0	140
2	0	0	100
3	0	0	180
4	0	0	130
5	0	0	160
6	0	0	150
7	0	0	140
8	0	0	142
9	0	0	184
10	0	0	160

APPROXIMATE WEIGHT OF MATERIAL (as measured by Govmark): 481 g/m²

FAILURE CRITERIA: For each individual specimen --

Afterflame	Drip Burn	Char Length
Exceeds 2.0 seconds	Exceeds 2.0 seconds	Exceeds 435 mm (17.1")

RETEST PROVISION: Test 5 additional specimens if only 1 specimen fails.

CONCLUSION: Based on the above Results and Failure Criteria, the item tested:

☒ Passes; ☐ Fails; ☐ Requires testing of 5 additional specimens

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by NFPA 701 - 2010 Edition Test Method #2 Flat Sheet Specimens.

Heather E. Roberts

AUTHORIZED SIGNATURE

THE GOVMARK ORGANIZATION, INC. / ec / *mg* (Page 1 of 2)

HEATHER E. ROBERTS



Received:09/02/2010	Completed:09/08/2010	Letter: S	her	P.O.#:	Test Report #:	2-84460-0-
Client's Identification	Style: Jetflex/ Normandy Pro. Content: Polyester. Finish: PVC. Weight:13 oz/yd ² . End Use: Sign, Banner & Billboard Media.					
Tested For: Jaime L. Giannantonio Ultraflex Systems Inc. 1578 Sussex Tpk., Bldg. #4 Randolph, NJ 07869				Key Test: NFPA 701-2010 TM#2 Flat 340 Tel: 1-(973)-664-6724 Ext: Fax: 1-(973)-627-8506		

PRECONDITIONING: ☒ 1 hr @ 220°F (Standard)
 ☐ 24 hrs @ 68±9°F (Alternate: Material shrinks/distorts @ 220°F)

REMARKS: Client requested that the restraining clamp binder clips be eliminated to replicate the provisions of the 1996 Test Method #1 version of this document.

CONVERSION FACTORS:
mm ÷ 25.4 = inches
g/m² ÷ 28.35 x .835 = oz/yd²



Received:09/02/2010	Completed:09/13/2010	Letter: S1	her	P.O.#:	Test Report #:	2-84460-1-
Client's Identification	Style: Jetflex/ Normandy Pro. Content: Polyester. Finish: PVC. Weight:13 oz/yd ² . End Use: Sign, Banner & Billboard Media.					
Tested For: Jaime L. Giannantonio			Key Test: NFPA 701-2010 TM#2 Flat WL		490	
Ultraflex Systems Inc. 1578 Sussex Tpk., Bldg. #4 Randolph, NJ 07869			Tel: 1-(973)-664-6724 Fax: 1-(973)-627-8506		Ext:	

PC:1H

TEST PERFORMED: NFPA 701 - Standard Methods of Fire Tests for Flame Propagation of Textiles and Films - 2010 Edition - Test Method #2 - Flat Sheet Specimens

SPECIMEN CONFIGURATION: ☒ Single Layer; ☐ Multi Layer

RESULTS REPORTED: ☐ Initially ☒ After 72 hours water leaching
☐ After 3 dry cleanings ☐ After 100 hours accelerated weathering
☐ After 5 launderings @ 160°F

RESULTS:

Length Specimen #	Afterflame (seconds)	Drip Burn (seconds)	Char Length (mm)
1	0	0	160
2	0	0	140
3	0	0	180
4	0	0	154
5	0	0	170
6	0	0	130
7	0	0	160
8	0	0	150
9	0	0	172
10	0	0	164

APPROXIMATE WEIGHT OF MATERIAL (as measured by Govmark): 481 g/m²

FAILURE CRITERIA: For each individual specimen --

Afterflame	Drip Burn	Char Length
Exceeds 2.0 seconds	Exceeds 2.0 seconds	Exceeds 435 mm (17.1")

RETEST PROVISION: Test 5 additional specimens if only 1 specimen fails.

CONCLUSION: Based on the above Results and Failure Criteria, the item tested:

☒ Passes; ☐ Fails; ☐ Requires testing of 5 additional specimens

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by NFPA 701 - 2010 Edition Test Method #2 Flat Sheet Specimens.

Heather E. Robertson

AUTHORIZED SIGNATURE

THE GOVMARK ORGANIZATION, INC. / ec (Page 1 of 2)

MS. HEATHER ROBERTSON SEP 17 2010



Received:09/02/2010	Completed:09/13/2010	Letter: S1	her	P.O.#:	Test Report #:	2-84460-1-
Client's Identification	Style: Jetflex/ Normandy Pro. Content: Polyester. Finish: PVC. Weight:13 oz/yd ² . End Use: Sign, Banner & Billboard Media.					
Tested For: Jaime L. Giannantonio			Key Test: NFPA 701-2010 TM#2 Flat WL			490
Ultraflex Systems Inc.			Tel: 1-(973)-664-6724			Ext:
1578 Sussex Tpk., Bldg. #4			Fax: 1-(973)-627-8506			
Randolph, NJ 07869						

PRECONDITIONING: ☒ 1 hr @ 220°F (Standard)
 ☐ 24 hrs @ 68±9°F (Alternate: Material shrinks/distorts @ 220°F)

REMARKS: Client requested that the restraining clamp binder clips be eliminated to replicate the provisions of the 1996 Test Method #1 version of this document.

CONVERSION FACTORS:
mm ÷ 25.4 = inches
g/m² ÷ 28.35 x .835 = oz/yd²

(Page 2 of 2)