

50600WOA Oasis™ Saturate

Wilflex™ Oasis Saturate is a wetting agent designed for use with Oasis inks when ink penetration is desired.

Highlights

- ▶ Improves ink penetration into fabric.
- ▶ Can be used to penetrate thin fabrics producing a front and back print simultaneously.
- ▶ Suitable for use when towel printing.

Printing Tips

- ▶ Recommended for use with Oasis Inks at a rate of 0.1%, up to 1% max by weight.
- ▶ Refer to Oasis base PIB.

Compliance

- ▶ Compliant with CPSIA 2008 (Consumer Product Safety Improvement Act) Section 101, Lead Content in Substrates (<100 ppm lead); 16 CFR, Part 1303, Lead in Paint (<90 ppm lead); and CPSIA 2008, Section 108, Phthalates (<0.1% DEHP, DBP, BBP, DINP, DIDP, DNOP).
- ▶ Non-PVC, Non-Phthalate.

Precautions


- ▶ Most substrates are suitable for printing; however, fibers which possess a low surface adhesion (e.g. polypropylene, silk, polyamide or wool) will require special care during drying and cure processes. Test all fabrics for color fixation and wash fastness before starting any production runs.
- ▶ Perform fusion tests before production. Failure to cure ink properly may result in poor wash fastness, inferior adhesion and unacceptable durability. Ink flash temperatures should be measured on the ink surface using an infrared thermometer sensor. Ink cure temperatures should be measured using a Thermoprobe placed directly in the wet ink film (printed) and verified on the production run substrate(s) and production equipment. It is the responsibility of the printer to determine that the correct ink has been selected for a specific substrate and the application processes meet your customer's standards or specifications./To avoid ink interaction in the image area, verify that the screen mesh is clean of previous ghost images. The image area must be clean and de-hazed.
- ▶ Excess additions of Oasis additives into Oasis inks may adversely affect ink properties.
- ▶ Containers must maintain air-tight seal when not in use.
- ▶ **NON-CONTAMINATION OF OASIS INKS:** Do not add or mix non-Oasis inks, additives or extenders with Oasis inks. All buckets, palette knives, stirring apparatus, squeegees, flood bars and screens must be cleaned properly and free of phthalates and PVC containing inks. Non-phthalate emulsions and pallet adhesives must be used. Failure to follow these precautions may cause phthalate contamination in violation of consumer protection laws and regulations.
- ▶ Any application not referred in this product information bulletin should be pre-tested or consultation sought with Wilflex Technical Services Department prior to printing.
- ▶ Email: techserviceswilflex@polyone.com

Recommended Parameters

Opacity *N/A*
 Bleed Resistance *N/A*
 Smooth Surface *N/A*
 Flash *N/A*
 Gloss *N/A*
 Printability *N/A*




Fabric Types
 Refer to Oasis base PIB.




Mesh
Counts: Refer to Oasis base PIB.
Tension: Refer to Oasis base PIB.



Squeegee
Durometer: Refer to Oasis base PIB.
Edge: Refer to Oasis base PIB.
Stroke: Refer to Oasis base PIB.
Angle: Refer to Oasis base PIB.



Water-Resistant Stencil
Direct: Refer to Oasis base PIB.
Capillary/Thick Film: *N/A*
Off-Contact: Refer to Oasis base PIB.
Emulsion-over-Mesh: Refer to Oasis base PIB.



Flash & Cure Temperatures
Flash: Refer to Oasis base PIB.
Cure: Refer to Oasis base PIB.



Pigment Loading
WPC: *N/A*



Oasis Additives
 Add into Oasis inks at a rate of 0.1%
 Do not exceed 1% max.
**All percentages listed at % by weight.*



Storage
 37-104°F (3-40°C).
 Use within one year of manufacture date.
 Keep containers sealed at all times.



Clean Up
 Warm Soap Water (Tap)
 Gentle Pressure



Health & Safety
MSDS: www.polyone.com or
 Contact your local CSR.

www.wilflex.com/pib

PolyOne Wilflex™ inks by PolyOne.

©2013 PolyOne Corporation All Rights Reserved. Effective 02/04/2013. Not all Wilflex products are available in every country. The information in this publication is based on information and experience believed reliable. Since many factors may affect processing for an application, processors must carry out their own tests and experiments to confirm suitability for intended use. You must make your own determination of suitability for your intended use and environmental acceptability, the safety and health of your employees, and purchasers of your product.