

AVIENT SPECIALTY INKS

INFINITE FX GLOW-IN-DARK / INTENSE KOSMIC GLOW

Avient™ Specialty Inks INFINITE FX GLOW-IN-DARK and INTENSE KOSMIC GLOW produce a high intensity, phosphorescent, greenish glow-in-the-dark effect with exposed to light and viewed in a darkened area. Intense Kosmic Glow inks provide high intensity and maintain a long duration. Infinite FX Glow-in-Dark inks provide high intensity for a shorter duration.

HIGHLIGHTS

- ▶ GLOW-IN-DARK | 2550
INTENSE KOSMIC GLOW | 2554
- ▶ Excellent glow properties and wash durability
- ▶ Produces a high intensity phosphorescent glow effect with long lasting afterglow
- ▶ Suitable for direct print or cold peel transfer application
- ▶ Ready-for-use or tintable

PRINTING TIPS

- ▶ Stir inks before printing
- ▶ Use consistent, high-tensioned screen mesh and sharp edged squeegees for best print results
- ▶ Best "glow" results when printed directly onto light colored fabric or over a light colored underlay when printing on dark fabric
- ▶ Intense Kosmic Glow is a state-of-the-art phosphorescent ink with maximum glow intensity and duration
- ▶ Tintable with plastisol colorants. See Pigment Loading section for suggested percentages. Limit the % colorant added to maintain best glow properties
- ▶ Avoid excess cure temperatures as this can damage the phosphorescent pigment
- ▶ For cold peel transfers on darks, use a coated release paper or polyester film. Print using 70 duro squeegee and recommended mesh counts, gel and then backed with light colored ink and followed by adhesive. Gel at 212°F (100°C) for 60 sec. Apply transfer with heat press at 340°F (170°C) for 10-12 sec at medium pressure. Verify process

COMPLIANCE

- ▶ Non-phthalate
- ▶ For individual compliance certifications and conformity statements, please visit www.avientspecialtyinks.com/services/compliance-support

PRECAUTIONS

The information above is given in good faith and does not release you from testing inks and fabrics to confirm suitability of substrate and application process to meet your customer standards and specifications



AVIENT
SPECIALTY
INKS

V1.00 (Modified: 05/10/2021)

2021, Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the information. Avient makes no warranties or guarantees respecting suitability of either Avient's products or the information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the information and/or use or handling of any product. AVIENT MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the information or products reflected by the information. This literature shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

PRODUCT INFORMATION BULLETIN



RECOMMENDED PARAMETERS



Fabric Types

100% cotton, cotton blends, some synthetics



Mesh

Count: 86-160 t/in (34-62 t/cm)
Tension: 25-35 n/cm²




Squeegee

Durometer: 60/90/60, 70/90/70, 60-70
Profile: Square, Sharp
Stroke: Medium flood, Medium stroke
Angle: 10-15%



Stencil

2 over 2
Off Contact: 1/16" (.2cm)
Emulsion Over Mesh: 15-20% or 35-70 microns



Flash & Cure

Flash: 220°F (105°C)
Cure: 320°F (160°C)



Pigment Loading

up to 5% Wilflex PC
up to 5% Wilflex EQ
up to 5% Wilflex MX/RIO
upto 5% Rutland C3 Boosters



Additives

K2915 CURABLE REDUCER - 5% max



Storage

65-90°F (18-32°C)
Avoid direct sunlight
Use within one year of receipt



Clean Up

Dispose unused ink responsibly.
Standard plastisol cleaners, press wash, or ink degradant



Health & Safety

Find SDS information here:
www.avient.com/resources/safety-data-sheets
or contact your local CSR

THIS PRODUCT IS BROUGHT TO YOU BY

NAZDAR
SOURCE ONE

VISIT US ONLINE
SourceOne.Nazdar.com

CALL US
888-578-5713

© 2023 Nazdar. All Rights Reserved.
Specifications subject to change without notice.