

RECOMMENDED FABRICS

100% Cotton
Cotton/Polyester Blends
Some polyester




INK APPLICATION

Metallic Shimmers should be used right from the container without any modifications. Stir well prior to each use.




ADDITIVES

If necessary: 1610 Curable Reducer (Add 1% to 5% by weight)



SCREEN MESH

86 to 110 t/in or 34-43 t/cm Monofilament for Gold and Silver.
25 to 61 t/in or 9 to 24 t/cm Monofilament for Crystalina.



EMULSION

Any direct or indirect solvent resistant emulsion.



SQUEEGEE

60-75 Durometer
Sharp or beveled edge.



CURE TEMPERATURES

325°F (163°C). The efficiency of the oven and length of heat tunnel will determine dwell time. Metals reflect heat, so adjust dwell time accordingly.



CLEAN-UP

Any environmentally friendly plastisol type screen wash.



PRODUCT PACKAGING

Quart, 1 gallon, 5 gallon containers



STORAGE OF INK CONTAINERS

65° to 90°F (18°C to 32°C) Avoid storage in direct sunlight. Keep containers well sealed



SDS

Refer to SDS prior to use

FEATURES

- **Crystalina Shimmer 1855**
- **Silver Shimmer 1856**
- **Gold Shimmer 1857**

AXEON™ Shimmers are used to produce a bright, sparkled look when printed. Add interest and bling to your designs! AXEON™ Shimmers print just like a traditional plastisol and designs made with Shimmers may be applied to light or dark fabrics.

SPOT FLASHING

This product will spot dry, with a very low after flash tack. Dwell time is dependent on the spot dryer used. In some cases, you may have to lower the heat of the spot cure unit because too much heat may actually make the ink tacky. When you spot dry, you are only partially fusing or gelling the surface of the ink. The ink should just be dry to the touch, with no lift off, but not totally fused. Totally fusing the underprint white may cause inter-coat adhesion problems with the inks printed on top of the white ink. Final fusing or curing will occur in the dryer. Failure to fuse ink properly may cause cracking poor adhesion and poor wash fastness.

IMPORTANT INFORMATION

1. The Shimmer inks are low bleed inks, not non-bleed inks. On some types of fabric, bleeding or dye migration may occur. Always test print the fabric to be printed before beginning production. It is best to do some long term testing on some fabrics to determine if they are going to bleed. Bleeding or dye migration may not occur immediately.
2. Thinning this product may reduce the metallic sparkle. Thinning this product may reduce the sparkle.
3. Print the Shimmer inks last in a design, when printing wet on wet, to avoid excessive pick-up of the ink.
4. Too high of a temperature in the dryer, above 350°F (177°C), may reduce the brilliance of the Shimmer inks.
5. For better adhesion on some fabrics it may be necessary to add the 900 Catalyst for proper adhesion.
6. The Shimmers will spot dry, with a very low after flash tack, in 2 to 8 seconds depending on the spot dryer used. This allows the inks to be printed earlier in a design when desired.
7. Print Shimmer last in the design to avoid excessive pick-up of the shimmer flakes.
8. The Gold and Silver Shimmers have good opacity on dark fabrics. However, in some instances, when printing through finer mesh counts, double hits with or without a flash may be needed.
9. Do not mix shimmers with opaque inks as they will block out or cover the Shimmer flakes.

For best durability of the Shimmers after they are applied, it is recommended that the garment be hand washed or machine washed (delicate cycle) inside out and line or air dried. Do not use bleach. Do not iron printed area. Test dryer temperatures and wash test printed product before and during a production run.

This ink and those in the Axeon product line are not formulated with PVC resin, nor are they intentionally added.

Care should be taken to not cross-contaminate the Axeon products with PVC containing products.

Do not use standard plastisol curable reducers with this or any of the Axeon products.

LEGAL DISCLAIMER

Recommendations and statements made are based on International Coatings' research and experience. Since International Coatings does not have any control over the conditions of use or storage of the product sold, International Coatings cannot guarantee the results obtained through use of its products. All products are sold and samples given without any representation of warranty, expressed or implied, of fitness for any particular purpose or otherwise, and upon condition that the buyer shall determine the suitability of the product for its own purpose. This applies also where rights of third parties are involved. It does not release the user from the obligation to test the suitability of the product for the intended purpose and application.

REV. 1600002