




# 7043 GUARDIAN GRAY™




**RECOMMENDED FABRICS**  
50/50 Cotton/Polyester Blends  
100% Polyesters



**INK APPLICATION**  
Guardian Gray 7043 must be printed without any modifications in order to maintain the best bleed resistance of the product




**ADDITIVES**  
Not recommended



**SCREEN MESH**  
83 - 160 t/in (32-63 t/cm)  
monofilament



**EMULSION**  
Any direct or indirect emulsion or capillary film in the 35 to 70 micron range



**SQUEEGEE**  
65-75 Durometer  
Sharp edge



**CURE TEMPERATURES**  
285°F-325°F (140°C-163°C) for 1 minute, dependent on dryer speed and temperature settings and top coat used



**CLEAN-UP**  
Any environment friendly plasti-sol screen wash



**PRODUCT PACKAGING**  
Quart, 1 gallon, 5 gallon, 30 gallon or 50 gallon containers



**STORAGE OF INK CONTAINERS**  
65° to 90°F (18°C to 32°C) Avoid storage in direct sunlight Keep containers well sealed



**SDS**  
Refer to SDS prior to use

## FEATURES

7043 Guardian Gray™ blocks dye migration on problem fabrics that contain polyester, including sublimated dyed fabrics.

7043 Guardian Gray™ can take a variety of top coats depending on application; from low cure products to regular temperature curing products.

7043 Guardian Gray™ offers superior bleed resistant properties, but on some problem fabrics it may be possible for bleeding or dye migration to occur.

## SPOT FLASHING

7043 Guardian Gray™ will spot dry, with a very low after flash tack. Dwell time is dependent on the spot dryer used. In some cases, you may have to lower the heat of the spot cure unit because too much heat may actually make the ink tacky. When you spot dry, you are only partially fusing or gelling the surface of the ink. The ink should be just dry to the touch, with no lift-off, but not totally fused. Totally fusing the underprint may cause inter-coat adhesion problems with the inks printed on top. Final fusing or curing should occur in the dryer.

## IMPORTANT INFORMATION

Always test for possible dye migration before beginning a production run. Bleeding or dye migration may not occur right away.

It is very important that 7043 Guardian Gray™ be exactly registered with any white or other color that is printed on top of the Guardian Gray in order to help insure maximum bleed resistance of the top color. If the color printed on top of Guardian Gray™ overlaps the Guardian Gray™ in any spot, that spot may show bleeding or dye migration.

Adding any reducers or additives can lower the bleed resistance, opacity or increase cure times of ink. **STIR** the ink prior to printing on press and after addition of reducers or additives.

Test dryer temperatures and wash test printed product before and during a production run.

## NOTE: FOR BEST RESULTS

For best print and blocking results, print two passes of 7043 Guardian Gray™ through a 110 mesh screen. Then in sequence, Print-Flash-Print-Top Coat using a low bleed white ink or other type of low bleed performance ink.

## LEGAL STUFF

Recommendations and statements made are based on International Coatings' research and experience. Since International Coatings does not have any control over the conditions of use or storage of the product sold, International Coatings cannot guarantee the results obtained through use of its products. All products are sold and samples given without any representation of warranty, expressed or implied, of fitness for any particular purpose or otherwise, and upon condition that the buyer shall determine the suitability of the product for its own purpose. This applies also where rights of third parties are involved. It does not release the user from the obligation to test the suitability of the product for the intended purpose and application.

REV. 1600001

13929 E. 166th St., Cerritos, CA 90703 • PH (800) 421-6971 or (562) 926-1010 • FAX (562) 926-9486 • E-mail [icinfo@iccink.com](mailto:icinfo@iccink.com) • [www.iccink.com](http://www.iccink.com)

THIS PRODUCT IS BROUGHT TO YOU BY



VISIT US ONLINE  
[SourceOne.Nazdar.com](http://SourceOne.Nazdar.com)

CALL US  
888-578-5713

© 2018 Nazdar. All Rights Reserved.  
Specifications subject to change without notice.