

**667702KI Special Mirror Silver Screen Ink is a solvent-based ink for printing second surface on transparent polycarbonate film. The ink film exhibits a mirror-like reflective surface when viewed through the top or first surface of the polycarbonate film.**

**Adhesion of the ink to substrates other than polycarbonate must be tested prior to any production run. The mirror silver ink is not compatible with laminating adhesives. See section on Overprint. The thoroughly dried ink film may be overprinted with Nazdar screen inks, including 9700 Series, 1800 Series and 2400 Series ink for further protection. Over-printing the mirror ink with other ink systems is not recommended.**

## Substrates

- Polycarbonate

Substrate recommendations are based on commonly available materials intended for the ink's specific market when the inks are processed according to this technical data. While technical information and advice on the use of this product is provided in good faith, the User bears sole responsibility for selecting the appropriate product for their end-use requirements. Reference the 'Quality Statement' at the end of this document.

## User Information

### Mesh

305 - 380 tpi (120 - 150 tpcm) monofilament polyester mesh for most applications.

### Stencil

Use direct emulsions and capillary films which are solvent resistant.

### Squeegee

70-80 durometer polyurethane squeegee.

### Coverage

Estimated 2,500 – 3,500 square feet (230 - 325 square meters) per gallon depending upon ink deposit. Reference [www.nazdar.com](http://www.nazdar.com) for examples of coverage calculations.

### Printing

667702KI Special Mirror Silver ink is formulated to be press ready. Add only enough ink to the screen to be able to print for 5-10 minutes. Add additional ink in small increments throughout the print run to maintain screen stability. Thoroughly mix the ink prior to printing. The ink must be mixed at low shear to prevent damaging the specialized pigment.

Maintain ink temperature at 65° - 90°F (18° - 32°C) for optimum print drying performance. Lower temperatures increase the ink viscosity,

impairing both flow and drying. Elevated temperatures lower the ink viscosity, reducing print definition, film thickness and opacity.

Pretest to determine optimum printing performance for a particular set of ink, substrate, screen, press, and drying variables/conditions.

Nazdar does not recommend inter-mixing of 667702KI with any other ink.

### Drying / Curing Parameters

The ink may be dried at room temperature or in a 140°F (60°C) oven for at least 15 minutes (drying time depends on mesh used and other factors affecting ink film thickness). Drying at higher temperatures may affect the mirror-like appearance. The ink must be thoroughly dried for optimal properties.

Due to varying ink deposits and production equipment, it is recommended that the printer evaluate the drying time and temperature that will allow the maximum reflectance for the specific application. Good air circulation is necessary to remove the vaporized solvents.

### Overprint

**Overprints:** The following Nazdar ink systems may be printed over a thoroughly dried 667702KI ink film: 9700, 1800, or 2400. Refer to each ink system's Technical Data Sheet for more information regarding either of these inks. Overprinting with a clear or solid color ink will provide some protection to the metallic. Due to the pigment load and nature of metallic pigments, the 667702KI may not exhibit satisfactory adhesion to the substrate and overprints may not pass cross hatch tape test. Overprinting with other ink systems may cause incompatibility which affects the mirror finish; test thoroughly.

# Nazdar 667702KI Special Mirror Silver Screen Ink



Due to the nature of the metallic pigments used in these types of the product, the layer of mirror silver may not pass tape and cross hatch tape tests. The pigment has the tendency to split or lift off upon removal of tape or adhesives from the printed surface making the mirror layer the weakest interface. Overprinting with other ink systems may cause incompatibility which affects the mirror finish; test thoroughly.

## Overprint Clears / Varnishes

Overprint Clears: the following overprint clear inks may be printed over a thoroughly dried 667702KI ink film: 9727 or 1527.

## Cleanup

Screen Wash (Prior to Reclaim): Use IMS201 Premium Graphic Screen Wash, IMS203 Economy Graphic Screen Wash, or IMS206 Graphic Auto Screen Wash.

Press Wash (On Press): Use IMS301 Premium Graphic Press Wash.

## Storage / Shelf Life

Store closed containers at temperatures between 65°-78°F (18°-25°C). Storing products outside of these recommendations may shorten their shelf life. Ink taken from the press should not be returned to the original container; store separately to avoid contaminating unused ink.

To obtain the official shelf life letter, Contact Nazdar Technical Service at [InkAnswers@nazdar.com](mailto:InkAnswers@nazdar.com) or see contact listing at the end of this document.

## General Information

### Ink Handling

All personnel mixing and handling these products must wear gloves and eye protection. Clean up spills immediately. If ink does come in contact with skin, wipe ink off with a clean, dry, absorbent cloth (do not use solvent or thinner). Wash the affected area with soap and water. Consult the applicable [Safety Data Sheet](#) (SDS / MSDS) for further instructions and warnings.

For assistance on a wide range of important regulatory issues, consult the following Regulatory Compliance Department link at <http://www.nazdar.com> or contact Nazdar Ink

Technologies - World Headquarters (see contact listing at the end of this document).

v 8 EN  
Ref: v 8 EN

## Manufacturer's Product Offering

Based on information from our raw material suppliers, these ink products are formulated to contain less than 0.06% lead. If exact heavy metal content is required, independent lab analysis is recommended.

## Packaging / Availability

Contact your Nazdar distributor for product availability and offering.

Item Number	Color
667702KI	Special Mirror Silver Screen Ink

## Cleaners / Clean Up

Item Number	Color
IMS201	Premium Graphic Screen Wash
IMS203	Economy Graphic Screen Wash
IMS206	Graphic Auto Screen Wash
IMS301	Premium Graphic Press Wash

## Nazdar Quality Statement

*Nazdar® stands behind the quality of this product. Nazdar® cannot, however, guarantee the finished results because Nazdar® exercises no control over individual operating conditions and production procedures. While technical information and advice on the use of this product is provided in good faith, the User bears sole responsibility for selecting the appropriate product for their end-use requirements. Users are also responsible for testing to determine that our product will perform as expected during the printed item's entire life-cycle from printing, post-print processing, and shipment to end-use. This product has been specially formulated for screen printing, and it has not been tested for application by any other method. Any liability associated with the use of this product is limited to the value of the product purchased from Nazdar®.*

## Nazdar Ink Technologies Offices

**Nazdar Ink Technologies** -World Headquarters  
8501 Hedge Lane Terrace  
Shawnee, KS 66227-3290 USA  
Toll Free US: 866.340.3579  
Tel: +1 913-422-1888  
Fax: +1 913-422-2296  
E-mail: [custserv@nazdar.com](mailto:custserv@nazdar.com)  
Technical Support E-mail: [InkAnswers@nazdar.com](mailto:InkAnswers@nazdar.com)

**Nazdar Limited** – England  
Battersea Road, Heaton Mersey  
Stockport, England SK4 3EE  
Tel: + 44 (0) 161-442-2111  
Fax: + 44 (0) 161-442-2001  
EMEA Technical Service E-mail:  
[technicalservicesuk@nazdar.com](mailto:technicalservicesuk@nazdar.com)

Solvent-Based Screen Ink

# Nazdar 667702KI Special Mirror Silver Screen Ink



**Nazdar – China**  
Room 17-04, Silver Centre  
1388, North Shan Xi Road  
Shanghai 200060 China  
Tel: 86-13818301261  
China E-mail: [aspac@nazdar.com](mailto:aspac@nazdar.com)

**Nazdar – Singapore**  
10, Changi South Street 3 #01-01  
Singapore 486147  
Tel: +65-65434920  
Fax: +65-65433690  
Asia E-mail: [aspac@nazdar.com](mailto:aspac@nazdar.com)

v 8 EN

Ref: v 8 EN

Solvent-Based Screen Ink