DESCRIPTION

PLUS 1-SR is a blue pigmented pre-sensitised photopolymer direct emulsion.

APPLICATIONS

PLUS 1-SR has been formulated for all high quality applications using solvent based and UV curing inks, including electronics, nameplates and graphics/POS.

WORKING INSTRUCTIONS

Unlike conventional diazo sensitised emulsions, PLUS 1-SR does not require sensitising prior to use.

SAFE LIGHT WORKING

PLUS 1-SR is sensitive to UV light and will 'fog' easily unless handled under good yellow safelight conditions. Similarly, coated screens must be handled under the same safelight conditions. Always store and use the product in original container, replacing lid after use.

ENVIRONMENTAL MANAGEMENT

Unused polyester/nylon: Autoprep and Universal Mesh Prep

Used polyester/nylon: Universal Mesh Prep or Auto Degreaser Concentrate 1:10

COATING & DRYING

PLUS 1-SR is intended for mesh counts between 55 and 165 threads/cm.

- 1. Apply 2 coats to the print side and 2 coats to squeegee side of the screen.
- 2. The screen should be dried at a maximum temperature of 30°C (86°F). Take care to store under dark or yellow light conditions.
- 3. Additional coatings may be applied to the underside of the screen with intermediate drying to improve printed edge quality.
- 4. The screen must be fully dried to ensure good exposure performance. If the screen has been stored outside of the drying cabinet it is good practice to re-dry prior to exposure to remove moisture that may be in the coating.



EXPOSURE

Exposure CORRECT EXPOSURE IS ESSENTIAL FOR OPTIMUM STENCIL PERFORMANCE. UNDEREXPOSURE WILL GIVE A WEAK STENCIL AND REDUCE RESISTANCE.

Remove dust from the surface of the stencil and tape positive in position. Place entire screen in a suitable vacuum frame and expose. We recommend use of the Autotype Exposure Calculator for test exposures to ascertain correct timing.

'Correct' exposure can be determined by hardness and 'through cure' of the stencil, and resolution of required detail. When correctly exposed, emulsion should not be easily removed from the squeegee side of the stencil when rubbed with a finger. We recommend the following as a guide in arriving at your best exposure time:

LAMP	DISTANCE	0	20	40	60	80	###	###	###	###
2kW metal halide	120 cm									
3kW metal halide	120 cm									
5kW metal halide	120 cm									
125W mercury vapour	50 cm									
UV floursecent tubes	10 cm									

Exposure time in seconds based on 2+2 coating on 120/cm (305/inch) amber monofilament polyester mesh.

WASHOUT & DRYING

Wash out the screen from both sides with a strong spray of water. Continue the washout until all parts of the image appear clean and sharp. Blot off surplus moisture with newsprint or a leather and dry at a maximum temperature of 30°C (86°F).

Spot out blemishes with Autotype Blue Filler or Regular Filler.

SHELF LIFE / STORAGE

Products should be kept in original packaging and stored away from direct sunlight or UV light sources. Under the recommended storage conditions, the optimum shelf life is 2 years at a storage temperature of 0-30°C (30-90°F).



STENCIL REMOVAL

Remove ink from the screen with Autosolve Graphics Screen Wash. Apply Autostrip (either Autostrip Gel or a solution of Autostrip Concentrate 1:20) to both sides of the screen. Leave standing for 5 minutes. The stencil can then be removed with a strong water jet or high pressure stripper. If a stain or ghost image still remains, use Autokleen Plus or Autohaze.

HEALTH AND SAFTEY INFORMATION

There are no hazards associated with the normal use of this product. However, splashes in the eyes may be irritating and very sensitive skin may need to be protected.

FIRE PRECAUTIONS

Non flammable.

SHELF LIFE / STORAGE

Flush with water.

FIRST AID

Eyes: Irrigate with water for 10 minutes.

Skin: Wash thoroughly.

Ingestion: Dilute with water and get medical advice.

ENVIRONMENTAL

This product is a mixture of water dispersible pigmented polymers. The polymers are polyvinylalcohols based photopolymers and/or plasticised polyvinylacetate with a dispersed pigments and surfactants. This product does not contain any materials regarded as ecotoxic or contained on the EC Black/Grey lists. Tests have shown no inhibition of activated sludge at typical effluent concentrations and the product may be regarded as drain safe and biodegradable.

SHELF LIFE & STORAGE

The emulsion should be stored between 5° and 20°C. Shelf life is 2 years when stored as recommended. Storage at higher temperatures will reduce shelf life.



PACKAGING

PLUS 1-SR is sold in sealed plastic containers.

Trade packs of 6 x 1 Litres and 4 x 4 Litres and 1 x 200 Litres.



SAFTERY & WARNING

MacDermid Autotype recommends that the company/operator read and review the Safety Data Sheets for the appropriate health and safety warnings before use.

Safety Data Sheets are available from MacDermid Autotype.

WASTE TREATMENT

Prior to using any recommendations or suggestions by MacDermid Autotype for waste treatment, the user is required to know the appropriate local/state/federal regulations for onsite or off-site treatment which may require permits. If there is any conflict regarding our recommendations, local/state/federal regulations take precedent.

CONTACT INFORMATION

To confirm this is the most recent issue, please contact MacDermid Autotype

Orders@macdermidconnect.com

North America MacDermid Autotype Inc. 5210 Phillip Lee Drive Atlanta, GA 30336, USA

(404) 696 4565 Orders@macdermidconnect.com **Europe MacDermid**

Autotype Ltd. Grove Road, Wantage, Oxon 0X12 7BZ, ÚK +44 (0) 1235 771111 OrdersEU@macdermidconnect.com Asia MacDermid

Autotype Pte Ltd. No, 20 Tuas Avenue 6, Singapore, 639307 +65 689 79670 sginfo@autotype.com

Also read carefully warning and safety information on the Safety Data Sheet. This data sheet contains technical information required for safe and economical operation of this product. READ IT THOROUGHLY PRIOR TO PRODUCT USE.

DISCLAIMER: All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. No statement or recommendation shall constitute a representation unless set forth in an agreement signed by officers of seller and manufacturer. NO WARRANTY OR MERCHANTABILITY OR WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE IS MADE. The following warranty is made in lieu of such warranties and all other warranties, express, implied, or statutory. Products are warranted to be free from defects in material and workmanship at the time sold. The sole obligation of seller and manufacturer under this warranty shall be to replace any product defective at the time sold. Under no circumstances shall manufacturer or seller be liable for any loss, damage or expense, direct or consequential, arising out of the inability to use the product. Notwithstanding the foregoing, if products are supplied in response to a customer request that specifies operating parameters beyond those stated above, or if products are used under conditions exceeding said parameters, the customer by acceptance or use thereof assumes all risk of product failure and of all direct, indirect and consequential damages that may result from use of the products under conditions, and agrees to exonerate, indemnify and hold harmless MacDarmid Incorporated thereform. No customic for product under conditions, and agrees to exonerate, indemnify and hold harmless MacDarmid Incorporated thereform. indemnify and hold harmless MacDermid Incorporated therefrom. No suggestion for product use nor anything contained herein shall be con-strued as a recommendation to use any product in infringement of any patent rights, and seller and manufacturer assume no responsibility or liability for any such infringement.

- ® Registered Trademark of MacDermid Performance Solutions. ™ Trademark of MacDermid Performance Solutions.
- © Platform Specialty Products Corporation and its subsidiaries 2016.

