



PLUS 6000

Product Data Sheet

DESCRIPTION

PLUS 6000 is a high quality, 44% solids, pigmented aqueous emulsion of water dispersible polymers and monomers, supplied with diazo powder sensitiser.

APPLICATIONS

PLUS 6000 is resistant to water-based, plastisol and ceramic tile printing inks.

PLUS 6000 is particularly recommended for applications where high print durability, good build and print quality on coarse meshes, and decoating after printing is required.

HAZARDS

The sensitiser powder is classified as 'harmful' by ingestion. Avoid breathing in dust. Rubber gloves and eye protection (goggles) should be worn, and if large quantities are handled, wear a dust mask. The product may be irritating to the skin, eyes or respiratory tract. Attention should be given to these safety precautions which isolate the user from any hazards. Keep in a dry, cool place away from heat, ignition and children's reach.

The emulsion is non-classified (both before and after sensitising), and there are no hazards associated with the normal use of this product. However, the product contains Chloromethylisothiazolinone (a biocide), which may produce an allergic reaction in some individuals. Splashes in the eyes may be irritating and very sensitive skin may need to be protected. Wear gloves and goggles as appropriate.

WARNINGS

Emulsion: May product an allergic reaction

Sensitiser: Harmful if swallowed

WORKING INSTRUCTIONS

Sensitising of Emulsion

NOTE: NEW 'DIRECT ADDITION' OF DIAZO

Handle PLUS 6000 under yellow fluorescent tubes or low wattage Tungsten light. PLUS 6000 is supplied as a two pack kit comprising the emulsion and powder sensitiser in a sachet.

WORKING INSTRUCTIONS - CONTINUED

Prior to sensitising read eHealth and Safety Information. Mix the two components as follows:

1. Cut the powder diazo sachet open using a pair of scissors (DO NOT OPEN WITH TEETH).
2. Add the powder diazo sensitiser DIRECTLY to the emulsion. (DO NOT DISSOLVE THE SENSITISER IN WATER OR ADD ADDITIONAL WATER TO THE EMULSION).
3. Stir thoroughly for approximately 2-3 minutes to ensure emulsion is sensitised throughout.
4. Allow the emulsion to de-gas for at least 15 minutes before use.

MESH PREPARATION

Unused polyester/nylon
Used polyester/nylon
Stainless Steel

Autoprep Gel and Universal Mesh Prep
Universal Mesh Prep

COATING & DRYING

Stand the screen on edge, angled away from the operator and, using a good quality coating trough, proceed as follows:

1. Apply 2 coats to the underside of the screen.
2. Apply 2 coats to squeegee side.
3. The screen should be dried horizontally, squeegee side up and stored under dark or yellow light conditions. Dry the screen at a maximum temperature of 30°C (86°F).
4. Additional coatings may be applied to the underside of the screen with intermediate drying.

EXPOSURE

CORRECT EXPOSURE IS ESSENTIAL FOR OPTIMUM STENCIL PERFORMANCE. UNDEREXPOSURE WILL GIVE A WEAK STENCIL AND REDUCE RESISTANCE.

Remove dust from the surface of the stencil and tape positive in position. Place entire screen in a suitable vacuum frame and expose. We recommend use of the Autotype Exposure Calculator for test exposures to ascertain correct timing. Exposure times below should be used as a guide:-

EXPOSURE TIME (MINUTES)*

LAMP	DISTANCE	0	1	2	3	4	5	6	7	8	9	10
2kW metal halide	120 cm											
3kW metal halide	120 cm											
5kW metal halide	120 cm											
125W mercury vapour	50 cm											
UV fluorescent tubes	10 cm											
Thorn Graph X	120 cm											

Based on 2+2 coating on 90/cm (230/inch) dyed monofilament polyester mesh.

WASHOUT & DRYING

Wash out the screen from both sides with a strong spray of water. Continue the washout until all parts of the image appear clean and sharp. Blot off surplus moisture with newsprint or a leather and dry at a maximum temperature of 30°C (86°F).

Spot out blemishes with sensitised emulsion.

STENCIL REMOVAL

Remove ink from the screen, with Autosolve screen cleaner. Apply Autostrip to both sides of the screen. Leave standing for 5 minutes. The stencil can then be removed with a strong water jet or high pressure stripper. If a stain or ghost image still remains, use Autokleen Plus.

FIRE PRECAUTIONS

The sensitizer powder will burn liberating toxic oxides of nitrogen. If burning extensively, breathing apparatus should be worn. Fires may be extinguished with water or foam.

SPILLAGE

Diazo sensitizer should be collected for authorised chemical disposal. The emulsion may be flushed to waste with extensive dilution. Large spillage should be absorbed in sand or sawdust and transferred to a safe area for disposal.

EXPOSURE TIME (MINUTES)*

Eyes: Irrigate with water for 15 minutes. Get medical advice.

Skin: Wash thoroughly with soap and water.

Ingestion: Wash out mouth. Administer emetic. Get medical attention.

SHELF LIFE & STORAGE

The unsensitised emulsion and sensitiser should be stored between 3° and 20°C for optimum shelf life.

Shelf life is 24 months.

ENVIRONMENTAL MORNING

This product is a mixture of water dispersible pigmented polymers. The polymers are polyvinylalcohols and/or plasticised polyvinylacetate with an insoluble pigment and surfactants. This product does not contain any materials regarded as ecotoxic or contained on the EC Black/Grey lists. Tests have shown no inhibition of activated sludge at typical effluent concentrations and the product may be regarded as drain safe and biodegradable.

DISPOSAL

Small quantities can be washed to foul waste. Larger quantities should be disposed of by an authorised industrial waste chemical contractor. Emulsion EWC Code: 08 04 08. Sensitiser EWC Code: 07 07 99.

PACKAGING

PLUS 6000 is sold in sealed plastic containers.

Trade packs of 6 x 1 Litres, 4 x 4 Litres, 1 x 200 Litres.

SAFETY & WARNING

MacDermid Autotype recommends that the company/operator read and review the Safety Data Sheets for the appropriate health and safety warnings before use.

Safety Data Sheets are available from MacDermid Autotype.

WASTE TREATMENT

Prior to using any recommendations or suggestions by MacDermid Autotype for waste treatment, the user is required to know the appropriate local/state/federal regulations for onsite or off-site treatment which may require permits. If there is any conflict regarding our recommendations, local/state/federal regulations take precedent.

CONTACT INFORMATION

To confirm this is the most recent issue, please contact MacDermid Autotype

Orders@macdermidconnect.com

North America

MacDermid Autotype Inc.
5210 Phillip Lee Drive
Atlanta, GA 30336, USA
(404) 696 4565
Orders@macdermidconnect.com

Europe MacDermid

Autotype Ltd.
Grove Road, Wantage, Oxon
OX12 7BZ, UK
+44 (0) 1235 771111
OrdersEU@macdermidconnect.com

Asia MacDermid

Autotype Pte Ltd.
No, 20 Tuas Avenue 6,
Singapore, 639307
+65 689 79670
sginfo@autotype.com

Also read carefully warning and safety information on the Safety Data Sheet. This data sheet contains technical information required for safe and economical operation of this product. READ IT THOROUGHLY PRIOR TO PRODUCT USE.

DISCLAIMER: All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. No statement or recommendation shall constitute a representation unless set forth in an agreement signed by officers of seller and manufacturer. NO WARRANTY OR MERCHANTABILITY OR WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE IS MADE. The following warranty is made in lieu of such warranties and all other warranties, express, implied, or statutory. Products are warranted to be free from defects in material and workmanship at the time sold. The sole obligation of seller and manufacturer under this warranty shall be to replace any product defective at the time sold. Under no circumstances shall manufacturer or seller be liable for any loss, damage or expense, direct or consequential, arising out of the inability to use the product. Notwithstanding the foregoing, if products are supplied in response to a customer request that specifies operating parameters beyond those stated above, or if products are used under conditions exceeding said parameters, the customer by acceptance or use thereof assumes all risk of product failure and of all direct, indirect and consequential damages that may result from use of the products under conditions, and agrees to exonerate, indemnify and hold harmless MacDermid Incorporated therefrom. No suggestion for product use nor anything contained herein shall be construed as a recommendation to use any product in infringement of any patent rights, and seller and manufacturer assume no responsibility or liability for any such infringement.

® Registered Trademark of MacDermid Performance Solutions. ™ Trademark of MacDermid Performance Solutions.

© Platform Specialty Products Corporation and its subsidiaries 2016.



By MacDermid Graphics Solutions