



- 1) **The user is responsible for determining the product's suitability, including adhesion and if needed, removal characteristics when used in applications other than listed specifically in this Performance Guide.**
- 2) **If there are any questions about applications, please contact your MACTac sales representative to discuss your requirements for recommendations.**
- 3) **If this is a printed Performance Guide it is an uncontrolled document. Please check the MACTac website for the latest, most up-to-date version.**

To achieve the best possible print quality, please make sure that the correct ICC profiles or printer settings are used. Profiles can be obtained from our Distributors or can be downloaded from [www.mactac.com/graphics](http://www.mactac.com/graphics). Printer and heater settings and ICC profiles can also be downloaded from some O.E.M. or software manufacturer's websites.

The ICC profiles are provided solely as a customer resource. Print environments, the individual nature of printing systems, inks and software can significantly affect output. It is the customer's responsibility to determine the suitability of any profile for use in their specific print environment.

#### **RECOMMENDATIONS:**

Always test your combination of B-free Gruv products, inks and laminating films prior to commercial use.

1. **Printing Conditions:** Print in conditioned pressroom at  $\pm 73^{\circ}\text{F}$  ( $23^{\circ}\text{C}$ ) and 50% RH. The maximum allowable ink saturation is 270%.
2. **Printing with UV inks both inkjet and Screen, will significantly reduce the stretch ability of this film and may result in cracking or lifting out of the deeper wall recesses and is not a warranty failure.**
3. **Drying Step:** It is **critical** the GV529BFD print is properly dried prior to cutting, lamination or application. We strongly recommend leaving the print *open to the air* (not rolled up in a tube) for a minimum of 24 hours prior to lamination or application. Residual solvents in the vinyl and adhesive will negatively affect the bubble free properties of the adhesive and can cause a significant build, or loss, in adhesion resulting in potential substrate or graphic failure and/or more residual adhesive being left behind upon removal. Additional hot air drying or IR drying will speed up the drying process and shorten the overall drying time.
4. **Laminating Conditions:** Ensure print is perfectly dry. Material must have 24 - 48 hr. drying time *open to the air*, not rolled up in a tube, prior to lamination or transportation. If the printed graphic is likely to be exposed to corrosive liquids, smoke, fumes, and highly polluted areas or there is a likelihood of scratching, it is highly recommended to laminate with **PERMACOLOR LUV** series (intermediate) or **PromoGard** (economy) overlaminating films.
5. **Not recommended for surfaces including, but not limited to** rubber and plastic, aged paint (chalking) and metals (corrosion or oxidation), improperly cured paint, surfaces with poor paint-to-surface adhesion, over existing graphics that must remain upon removal, oily surfaces, unpainted wood, etc.
6. **Transportation Conditions:** To allow for easy transportation, B-free Gruv series can be rolled up, with the image out, with a minimum diameter of 6 inches (15cm). When the image is not protected by an overlaminate, make sure the print is completely dry and protected in a plastic bag. During transportation or storage, avoid exposing them to extreme temperature and humidity changes.

#### **SHELF LIFE:**

2 year from Date of Manufacture when stored at 60 to 77°F (15/25°C) and 50% relative humidity in the original package.

*\* Values given are typical and are not necessarily for use in specification.*

**CALL 1-800-401-5005 for additional product information**

**IMPORTANT NOTICE:** The information given and the recommendations made herein are based on our research and are believed to be accurate, but no guarantee of their accuracy or completeness is made. In every case, user shall determine before using any product in full scale production, or in any way, whether such product is suitable for user's intended use for their particular purpose under their own operating conditions. User assumes all risk and liability whatsoever in connection with their use of any product. The products discussed herein are sold without any warranty as to merchantability or fitness for a particular purpose, or any other warranty, express or implied. No representative of ours has any authority to waive or change the foregoing provisions, and no statement or recommendation not contained herein shall have any force of effect unless in an agreement signed by the officers of seller and manufacturer. Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute a permission, inducement or recommendation to practice any invention covered by any patent without authority from the owner of the patent. The following is made in lieu of all warranties, express or implied: Seller's and manufacturer's only obligation shall be to replace or credit such quantity of the product proved to be defective at its discretion.

<sup>TM</sup> Trademark of Morgan Adhesives Company.

© Registered Trademark of Morgan Adhesives Company.  
[www.MACTac.com](http://www.MACTac.com)



A Bemis Company

THIS PRODUCT IS BROUGHT TO YOU BY

**NAZDAR**  
SOURCEONE

VISIT US ONLINE  
[SourceOne.Nazdar.com](http://SourceOne.Nazdar.com)

CALL US  
888-578-5713

© 2022 Nazdar. All Rights Reserved.  
Specifications subject to change without notice.