



MagnaPrint® Chalkboard

Chalkboard Effect

MagnaPrint® Chalkboard is a ready made, elastic binder specially formulated to allow the wearer to draw on the printed area using chalks. Chalks can be removed with a damp cloth or in the washing machine.

Application

Printing is best undertaken using 43 – 61 (110-160) mesh screens with rectangular profile squeegees on preheated pallets (70°C /186°F). After printing the garment/panel should be cured, ideally for 2 -2½ min @ 165° C (330°F).

SPECIFICATION



FABRIC TYPESCotton / Poly Cotton blends



MESH 43-61T (110 - 160) Mesh



SQUEEGEE Medium 65 Shore Rectangular



STENCIL Water resistant emulsion



CURE TEMPERATURE 2-2½ Minutes at 165°C (330°F)



PIGMENT LOADING
Up to 6% MagnaPrint® Eco
Pigments



ADDITIVESAdvancePrint, Crosslinker
100, Softener TS Conc



STORAGE

In cool place properly closed: >5c (40F) <25c (77F)



HEALTH & SAFETYMSDS available upon request



CLEAN UP

Wash off screen using water and mild detergent

All information is given in good faith but without warranty. They do not release you from testing our products as to their suitability for the intended processes and uses.



226 731751 F: 00 44 (0) 1226 731752 E: info@magnacolours.com www.magnacolours.com Company registered in England No. 01378495, VAT No. GB 997 3172 70

