



MagnaPrint® Crackle Range

Vintage Crackle Effect – Crack by Hand

The MagnaPrint® Crackle range is a fully aqueous ready to use printing pastes. The range consists of a CLEAR and a WHITE designed to give a print effect with a “cracked, aged” appearance on knitted/stretchy fabrics.

MagnaPrint® Eco Pigments can be added in order to achieve a desired shade. The WHITE may also be used pure to give a white effect.

Application

The MagnaPrint® Crackle range should be printed through an open mesh screen. The thicker the ink deposit the better the crack effect achieved.

After curing MagnaPrint® Crackle printed area should be stretched to achieve the “cracked” effect.

After printing the garment / panel should be dried and cured, ideally for 2½ - 3 mins at 165°C (330°F).

SPECIFICATION



FABRIC TYPES
Cotton / Poly Cotton



MESH
15-43T (38-110)



SQUEEGEE
Medium 65 Shore
Rectangular



STENCIL
Water resistant emulsion



CURE TEMPERATURE
2½-3 Minutes at 165°C
(330°F)



PIGMENT LOADING
Up to 6% MagnaPrint Eco
Pigment



ADDITIVES
Retardent Gel, Crosslinker
100



STORAGE
In cool place properly closed:
>5c (40F) <25c (77F)



HEALTH & SAFETY
MSDS available upon
request



CLEAN UP
Wash off screen using water
and mild detergent

All information is given in good faith but without warranty. They do not release you from testing our products as to their suitability for the intended processes and uses.



MagnaColours® Limited
Upper Cliffe Road,
Dodworth Business Park,
Barnsley, S75 3SP, UK

T: 00 44 (0) 1226 731751
F: 00 44 (0) 1226 731752
E: info@magnacolours.com
www.magnacolours.com

Company registered in
England No. 01378495,
VAT No. GB 997 3172 70