

The 60015820CV UV Tamper Proof Clear is to be printed on polycarbonate labels used in security applications. Labels are generally printed sub-surface on transparent film. In the event of tampering or attempts to remove the label, labels printed with this clear will be destroyed.

Overview

Print 60015820CV Tamper-Proof Clear in a graphic pattern (such as the word “void”) in the graphic area.

Use 3400 Series inks for graphic printing. 3400 inks (with 5% NB80 Adhesion Promoter) may be printed over HP Indigo digital offset prints. Refer to the 3400 Series Technical Data Sheet for processing information.

Possible label constructions are the following:

- UV Tamper Proof Clear, 3400 ink, laminating adhesive
- 3400 inks, UV Tamper Proof Clear, 3400 inks, laminating adhesive
- HP Indigo digital offset print, UV Tamper Proof Clear, 3400 white with 5% NB80 Adhesion Promoter as background, laminating adhesive

The printer is responsible for testing print and ink combinations for satisfactory performance in the end use environment for a particular label.

Substrates

- Polycarbonate

Substrate recommendation is based on commonly available materials intended for the ink’s specific market when the inks are processed according to this technical data. While technical information and advice on the use of this product is provided in good faith, the User bears sole responsibility for selecting the appropriate product for their end-use requirements. Reference the ‘Quality Statement’ at the end of this document.

User Information

Mesh

305-380 tpi (120-150 tpcm) monofilament polyester mesh for most applications.

Stencil

Use direct emulsions and capillary films which are solvent resistant and UV compatible.

Squeegee

70-80 durometer polyurethane squeegee.

Coverage

Estimated 2,000 – 3,500 square feet (185 – 325 square meters) per gallon depending upon ink deposit. Reference www.nazdar.com for examples of coverage calculations.

Printing

60015820CV is formulated to be press ready. Thoroughly mix the ink prior to printing. Improper mixing can lead to inconsistent ink performance.

Maintain ink temperature at 65°-90°F (18°-32°C) for optimum print and cure performance. Pretest to determine optimum printing/curing parameters for proper performance.

The ink can be affected by stray UV light. Be aware of skylights, windows and overhead lights curing the ink in the screen; light filters are recommended. Leaving a container uncovered may result in the ink’s surface forming a “skin”, caused by reaction with ambient lighting. Keep containers covered.

Nazdar does not recommend inter-mixing of 60015820CV with other inks.

Cure Parameters

60015820CV cures when exposed to a single medium pressure mercury vapor lamp emitting millijoules (mJ) and milliwatts (mW) of:

150+ mJ/cm² @ 600+ mW/cm² UVA

These guidelines are intended only as a starting point for determining cure parameters, which must be determined under actual production conditions. “Undercuring” the ink may result in poor adhesion, lower block resistance, and higher residual odor.

These guidelines are representative of measurements taken using an EIT® UVICURE® Plus radiometer measuring the UVA bandwidth (320-390 nm). To obtain accurate mW readings with the UVICURE® Plus, reduce the belt speed to less than 40 ft/min.

UV Screen Ink

Nazdar 60015820CV UV Tamper Proof Clear

Common Performance Additives

When required, any additives should be thoroughly mixed before each use. Prior to production, test any additive adjustment to the ink. Ink containing additives should not be mixed with other inks.

Example for additives: Ink at 100g with 8% of an additive is calculated as:

$$100\text{g ink} + 8\text{g additive} = 108\text{g total}$$

Reducer: Use RE306 Reducer to reduce the viscosity of the ink. Add up to 10% by weight. Over reduction can reduce film thickness and adversely affect cure.

Cleanup

Screen Wash (Prior to Reclaim): Use IMS201 Premium Graphic Screen Wash, IMS203 Economy Graphic Screen Wash, or IMS206 Graphic Auto Screen Wash.

Press Wash (On Press): Use IMS301 Premium Graphic Press Wash.

Storage / Shelf Life

Store closed containers at temperatures between 65°-78°F (18°-25°C). Storing products outside of these recommendations may shorten their shelf life. Ink taken from the press should not be returned to the original container; store separately to avoid contaminating unused ink.

60015820CV supplied 1 gallon (4/5 kilo) containers or smaller are useable for a period of at least 24 months from the date of manufacture. Inks packaged in 5 gallon or greater (20 kilo or greater) containers may have a significantly reduced shelf life. For more detail pertaining to the shelf life of Nazdar's ink products, contact Nazdar Technical Service at InkAnswers@nazdar.com or see contact listing at the end of this document.

General Information

Ink Handling

Wear gloves and barrier cream to prevent direct skin contact. Safety glasses are suggested in areas where ink may be splashed. If ink does come in contact with skin, wipe ink off with a clean, dry cloth (do not use solvent or reducer). Wash the affected area with soap and water. Consult the

applicable [Safety Data Sheet](#) (SDS / MSDS) for further instructions and warnings.

60015820CV is a one-part, 100% solids UV-curable screen printing ink and does not contain N-vinyl-2-pyrrolidone (trade name V-Pyrol®).

For assistance on a wide range of important regulatory issues, consult the following Regulatory Compliance Department link at <http://www.nazdar.com> or contact Nazdar Ink Technologies - World Headquarters (see contact listing at the end of this document).

Adhesion Testing

Even when recommended UV energy output levels are achieved, it is imperative to check the degree of cure on a **cooled down** print:

1. Touch of ink surface – the ink surface should be smooth.
2. Thumb twist – the ink surface should not mar or smudge.

Manufacturer's Product Offering

Based on information from our raw material suppliers, this ink product is formulated to contain less than 0.06% lead. If exact heavy metal content is required, independent lab analysis is recommended.

Packaging / Availability

Contact your Nazdar distributor for product availability and offering.

Standard Ink

Item Number	Color
60015820CV	UV Tamper Proof Clear

Additives / Reducers

Item Number	Item Description
RE306	Reducer

Cleaners / Clean Up

Item Number	Item Description
IMS201	Premium Graphic Screen Wash
IMS203	Economy Graphic Screen Wash
IMS206	Graphic Auto Screen Wash
IMS301	Premium Graphic Press Wash

Nazdar Quality Statement

Nazdar® stands behind the quality of this product. Nazdar® cannot, however, guarantee the finished results because

Nazdar 60015820CV UV Tamper Proof Clear

Nazdar® exercises no control over individual operating conditions and production procedures. While technical information and advice on the use of this product is provided in good faith, the User bears sole responsibility for selecting the appropriate product for their end-use requirements. Users are also responsible for testing to determine that our product will perform as expected during the printed item's entire life-cycle from printing, post-print processing, and shipment to end-use. This product has been specially formulated for screen printing, and it has not been tested for application by any other method. Any liability associated with the use of this product is limited to the value of the product purchased from Nazdar®.

v 3 EN

Ref: v 3 EN

Nazdar Ink Technologies Offices

Nazdar Ink Technologies -World Headquarters

8501 Hedge Lane Terrace
Shawnee, KS 66227-3290 USA
Toll Free US: 866-340-3579
Tel: +1 913-422-1888
Fax: +1 913-422-2296
E-mail: custserv@nazdar.com
Technical Support E-mail: InkAnswers@Nazdar.com

Nazdar Limited – EMEA

Battersea Road, Heaton Mersey
Stockport, England SK4 3EE
Tel: + 44 (0)-161-442-2111
Fax: + 44 (0)-161-442-2001
EMEA Technical Service E-mail:
technicalservicesuk@nazdar.com

Nazdar – China

Room 17-04, Silver Centre
1388, North Shan Xi Road
Shanghai 200060 China
Tel: +86-13818301261
E-mail: aspac@nazdar.com

Nazdar – Asia Pacific

10, Changi South Street 3 #01-01
Singapore 486147
Tel: +65-65434920
Fax: +65-65433690
E-mail: aspac@nazdar.com