

# Nazdar NSC42C & NSC42F Nitrogen Texture Clear UV Screen Ink

NSC42C Nitrogen TC Coarse and NSC42F Nitrogen TC Fine UV Screen Inks are specifically designed for use with germicidal lamps in an inert atmosphere to give a decorative textured effect on first surface polycarbonate for membrane overlay applications.

## Substrates

- Polycarbonate

Substrate recommendation is based on commonly available materials intended for the ink's specific market when the inks are processed according to this technical data. While technical information and advice on the use of this product is provided in good faith, the User bears sole responsibility for selecting the appropriate product for their end-use requirements. Reference the 'Quality Statement' at the end of this document.

## User Information

### Mesh

255-380 tpi (100-150 tpcm) monofilament polyester mesh for most applications.

### Stencil

Use direct emulsions and capillary films which are solvent resistant and UV compatible.

### Squeegee

70-80 durometer polyurethane squeegee.

### Coverage

Estimated 2,500 – 3,500 square feet (230 – 325 square meters) per gallon depending upon ink deposit.

### Printing

The NSC42C produces a coarse texture finish while NSC42F produces a fine texture. A medium texture is achieved when blending the NSC42C and NSC42F. Both inks are formulated to be press ready. Thoroughly mix the ink prior to printing.

Maintain ink temperature at 65°-90°F (18°-32°C) for optimum print and cure performance. Lower temperatures increase the ink viscosity, impairing flow and increasing film thickness. Elevated temperatures lower the ink viscosity and film thickness.

Pretest to determine optimum printing parameters for a particular set of ink, substrate, screen, press, and curing variables/conditions.

The ink can be affected by stray UV light. Be aware of skylights, windows and overhead lights

curing the ink in the screen; light filters are recommended. Leaving a container uncovered may result in the ink's surface forming a "skin", caused by reaction with ambient lighting. Keep containers covered.

### Cure Parameters

NSC42C and NSC42F cure in a nitrogen unit at 15 to 20 fpm when initially exposed to a germicidal lamp in an inert atmosphere and immediately cured with diffused lamps with nitrogen or with focused bulbs without nitrogen.

The appearance of the texture can vary depending on the amount of reducer, nitrogen flow, ink deposit, substrate used, belt speed, curing unit heat and wattage output.

Testing using actual production equipment must be done prior to any production run.

### Common Performance Additives

When required, any additives should be thoroughly mixed before each use. Prior to production, test any additive adjustment to the ink. Inks containing additives should not be mixed with other inks.

Example for additives: Ink at 100g with 8% of an additive is calculated as:

$$100\text{g ink} + 8\text{g additive} = 108\text{g total}$$

Reducer: Use RE307 Reducer to reduce the viscosity of these inks. Add up to 10% by weight.

### Cleanup

Screen Wash (Prior to Reclaim): Use IMS201 Premium Graphic Screen Wash, IMS203 Economy Graphic Screen Wash, or IMS206 Graphic Auto Screen Wash.

Press Wash (On Press): Use IMS301 Premium Graphic Press Wash.

### Storage / Shelf Life

Store closed containers at temperatures between 65°-78°F (18°-25°C). Storing products outside of these recommendations may shorten their shelf life. Ink taken from the press should not be

# Nazdar NSC42C & NSC42F Nitrogen Texture Clear UV Screen Ink



returned to the original container; store separately to avoid contaminating unused ink.

For information pertaining to the shelf life of Nazdar's ink products, contact Nazdar Technical Service at [InkAnswers@nazdar.com](mailto:InkAnswers@nazdar.com) or see contact listing at the end of this document.

## General Information

### Ink Handling

Wear gloves and barrier cream to prevent direct skin contact. Safety glasses are suggested in areas where ink may be splashed. If ink does come in contact with skin, wipe ink off with a clean, dry cloth (do not use solvent or reducer). Wash the affected area with soap and water. Consult the applicable [Safety Data Sheet](#) (SDS / MSDS) for further instructions and warnings.

For assistance on a wide range of important regulatory issues, consult the following Regulatory Compliance Department link at <http://www.nazdar.com> or contact Nazdar Ink Technologies - World Headquarters (see contact listing at the end of this document).

### Adhesion Testing

Even when recommended UV energy output levels are achieved, it is imperative to check the degree of cure on a **cooled down** print:

1. Touch of ink surface – the ink surface should be smooth.
2. Thumb twist – the ink surface should not mar or smudge.
3. Scratch surface – the ink surface should resist scratching.
4. Cross hatch tape test – per the ASTM D-3359 method, use a cross hatch tool or a sharp knife to cut through ink film only; then apply 3M #600 clear tape on cut area, rub down, and rip off at a 180 degree angle. Ink should only come off in actual cut areas.

## Manufacturer's Product Offering

Based on information from our raw material suppliers, these ink products are formulated to contain less than 0.06% lead. If exact heavy metal content is required, independent lab analysis is recommended.

## Packaging / Availability

Contact your Nazdar distributor for product availability and offering.

### Standard Ink Items

Item Number	Color
NSC42C	Nitrogen TC Coarse
NSC42F	Nitrogen TC Fine

### Additives / Reducers

Item Number	Item Description
RE307	Reducer

### Cleaners / Clean Up

Item Number	Item Description
IMS201	Premium Graphic Screen Wash
IMS203	Economy Graphic Screen Wash
IMS206	Graphic Auto Screen Wash
IMS301	Premium Graphic Press Wash

## Nazdar Quality Statement

*Nazdar® stands behind the quality of this product. Nazdar® cannot, however, guarantee the finished results because Nazdar® exercises no control over individual operating conditions and production procedures. While technical information and advice on the use of this product is provided in good faith, the User bears sole responsibility for selecting the appropriate product for their end-use requirements. Users are also responsible for testing to determine that our product will perform as expected during the printed item's entire life-cycle from printing, post-print processing, and shipment to end-use. This product has been specially formulated for screen printing, and it has not been tested for application by any other method. Any liability associated with the use of this product is limited to the value of the product purchased from Nazdar®.*

## Nazdar Ink Technologies Offices

**Nazdar Ink Technologies** -World Headquarters  
 8501 Hedge Lane Terrace  
 Shawnee, KS 66227-3290 USA  
 Toll Free US: 866-340-3579  
 Tel: +1 913-422-1888  
 Fax: +1 913-422-2296  
 E-mail: [custserv@nazdar.com](mailto:custserv@nazdar.com)  
 Technical Support E-mail: [InkAnswers@Nazdar.com](mailto:InkAnswers@Nazdar.com)

**Nazdar Limited** – EMEA  
 Batterssea Road, Heaton Mersey  
 Stockport, England SK4 3EE  
 Tel: + 44 (0)-161-442-2111  
 Fax: + 44 (0)-161-442-2001  
 EMEA Technical Service E-mail:  
[technicalservicesuk@nazdar.com](mailto:technicalservicesuk@nazdar.com)

UV Screen Ink

# Nazdar NSC42C & NSC42F Nitrogen Texture Clear UV Screen Ink



**Nazdar – China**  
Room 17-04, Silver Centre  
1388, North Shan Xi Road  
Shanghai 200060 China  
Tel: +86-13818301261  
E-mail: [aspac@nazdar.com](mailto:aspac@nazdar.com)

**Nazdar – Asia Pacific**  
10, Changi South Street 3 #01-01  
Singapore 486147  
Tel: +65-65434920  
Fax: +65-65433690  
E-mail: [aspac@nazdar.com](mailto:aspac@nazdar.com)

v 6 EN

Ref: v 6 EN

UV Screen Ink