

Technical Data Sheet

DSS 12oz Blockout

DSS 12oz. Blockout is a 12 oz. smooth, two sided blockout banner material that delivers similar quality printing results on both sides. DSS is compatible for use with eco solvent, latex, screen, solvent and UV inks. It is best suited for indoor applications where complete banner opacity is needed. With its unique low curl formula, DSS 12oz Blockout is perfect for pop-up or scrolling banner stands, tradeshow and event graphics, POP and any hanging banner or sign. Widths range from 38" to 126".

Material Details

CHARACTERISTICS	TEST METHOD	METRIC	ENGLISH	
Support Cloth	DIN ISO 2076	Polyester	Polyester	
Yarn dtex	DIN EN ISO 2060	300 x 300 dtex	300 x 300 denier	
Type of Coating	N/A	PVC	PVC	
Total Weight	DIN53352 BS3424 Method 5A	410 g/m ²	12 oz/yd ²	
Tensile Strength	DIN 53352 BS3424	776 x 796 N/5cm	88.6 X 90.9 lbs/in	
Tear Strength (warp/weft)	DIN 53356 BS3424	75.4 x 80.8 N/5cm	16.9 X 18.2 lbs/in	
Flame Resistance	DIN 75200	NFPA-701, Title 19		
Low Temperature (No Crack at:)	DIN 53357 BS3425 Method 10	Low at -10℃	Low at 10℉	
RF Weldable (Heat Sealable)	DIN 53354	Yes	Yes	
Fungus Resistant	ASTM G21	Yes		
Applications				

	Back-lit	Banner	Billboard	Block-out	Building Wrap	Display Systems	Truckside
Applications							

Ink Printability

Solvent	Eco Solvent	UV	Latex	Screen Printing	Dye Transfer	Dye Direct
			□*			

Available Sizes

Metric (m)	English (inches)
0.965, 1.29, 1.37, 1.60, 2.03, 2.60, 3.22	38, 39, 51, 54, 63, 80, 102, 126

Ultraflex Mexico

Mexico City, 08400

Key: ■ - Excellent □ - Good * one side only

The information on physical and chemical characteristics is based upon tests believed to be reliable. The values are intended only as a source of information. A legally binding guarantee of specific properties is not to be inferred from our specifications. They are given without guaranty and do not constitute a warranty. The purchaser should independently determine, prior to use, the suitability of this material for his/her specific purpose. (Data represents averages and is not intended for use as a specification.)

www.ultrafleXX.com Updated: 02/2012 Ultraflex Headquarters 1578 Sussex Turnpike, Building 4 Randolph, NJ 07869 P. 973-627-8608 F. 973-627-8506 Ultraflex Europe Ltd. Hardwick Rd Industrial Park Great Gransden Bedfordshire, England SG193BJ P. +44 1767 677100 F. +44 1767 677190

VISIT US ONLINE SourceOne.Nazdar.com CALL US 888-578-5713 © 2015 Nazdar. All Rights Reserved. Specifications subject to change without notice.

P. +52 5531-823-632 F. +52 5558-037-809

Avena 316-B Col. Granjas Mexico