

C 11480HTBright Tiger

Wilflex™ Bright Tiger is an extremely true, optically bright white ink formulated to give excellent printability across a range of screen printing applications. Bright Tiger's excellent opacity, fiber mat down, low gloss level, and good flash properties permit it to be utilized as both a stand-alone and an underbase white.

Highlights

- ▶ Compliant with CPSIA (Consumer Product Safety Improvement Act) 2008
 - ▶ Section 101, Lead Content in Substrates (<300 ppm lead);
 - ▶ 16 CFR, Part 1303, Lead in Paint (<90 ppm lead).
- ▶ For use on cotton and cotton blends
- ▶ Optically bright white
- ▶ Opaque
- ▶ Good Flash Properties
- ▶ Matte finish
- ▶ Prints through fine meshes
- ▶ Use as a first-down, underbase flash white or an overprint stand-alone white.
- ▶ Good bleed resistance
- ▶ Odorless

Printing Tips

- ▶ For best results, follow the recommended Printing Parameters.
- ▶ For one-hit opacity through coarse meshes, use a coating procedure that builds a thick, even stencil to ensure a good column height of ink.
- ▶ Avoid excessive squeegee pressure.
- ▶ Due to differences in power, height above ink film and efficiency of the flash drying unit, specific dwell time cannot be given
- ▶ To increase production speeds, use finer mesh counts for the flash plate to decrease gel time. Set flash dwell times on heated pallets to simulate production. Adjust your settings so that the ink is just dry to the touch.
- ▶ Use consistent, high tensioned screen mesh to optimize performance properties.

Precautions

- ▶ Perform fusion tests before production. Failure to cure ink properly may result in poor wash fastness, inferior adhesion and unacceptable durability. Ink gel and cure temperatures should be measured using a Thermoprobe placed directly in the wet ink film and verified on the production run substrate(s) and production equipment. It is the responsibility of the printer to determine that the correct ink has been selected for a specific substrate and the application processes meet your customer's standards or specifications.
- ▶ Pre-test on light colored or stone washed garments. Avoid stacking printed garments hot because such colors are more prone to color distortion. Fabric and dye characteristics can vary between manufacturers and from dye lot to lot.
- ▶ Avoid over flashing as it can result in poor inter-coat adhesion of colors.
- ▶ Avoid polyester-based fabrics where dye migration will occur.
- ▶ Reducing viscosity will adversely affect opacity.
- ▶ Stir plastisols before printing.
- ▶ Do not dry clean, bleach or iron printed area.
- ▶ Any application not referred in this product bulletin should be pre-tested or consultation sought with Technical Services Department prior to printing.
- ▶ Email: techserviceswilflex@polyone.com

PolyOne Wilflex™ inks by PolyOne.

©2009 PolyOne Corporation All Rights Reserved. Effective 5/05/2009. Not all Wilflex products are available in every country. The information in this publication is based on information and experience believed reliable. Since many factors may affect processing for an application, processors must carry out their own tests and experiments to confirm suitability for intended use. You must make your own determination of suitability for your intended use and environmental acceptability, the safety and health of your employees, and purchasers of your product.

Printing Parameters

Opacity	8	
Bleed Resistance	8	
Smooth Surface	8	
Flash	9	
Gloss	4	
Printability	9	




Fabric Types
100% cotton, cotton blends, some synthetics




Mesh
Counts: Darks - 86-125 t/in (34-48 t/cm)
Underbase - 140-230 t/in (55-90 t/cm)
Fine Line - 195 to 305 t/in (77-120 t/cm)
Tension: 25-35 n/cm² recommended



Squeegee
Durometer: 60-90, 70/90, 70/90/70
Edge: Rounded for coarse mesh, Sharp for finer mesh
Stroke: Hard flood, fast print
Avoid excess pressure



Stencil
Direct: over22
Capillary/thick film: N/A
Off contact: 1/16" (.2 cm)



Gel/Cure Temperatures
Gel: 160-180 F (71-82 C)
Cure: 320 F (160 C) entire film



Pigment Loading
N/A



Additives
Extender: None recommended
Reducer: 3% max by weight
10025VB QEC Viscosity Buster.



Storage
65°-90°F (18°-32°C)
Avoid direct sun.
Use within one year of receipt.



Clean Up
Wilflex Screen Wash



Health & Safety
MSDS: www.polyone.com

www.wilflex.com/pib