

**Product Information Bulletin** 

## 15000PFB Epic Mixing Base

Wilflex™ Epic Mixing Base is specially formulated non-phthalate base for Epic PC and Epic EQualizer mixing systems. Designed for high productivity, wet-on-wet printing, Epic Mixing Base offers exceptional print qualities for both manual and automatic prints.

#### Highlights Dalþ

- Matte finish
- ▶Clean, bright colors when mixed with Epic PCs or Epic EQs.
- Excellent flash properties.
- Ideal for overprinting onto a flashed white underbase.
- Build-up resistant for high productivity printing.

# **Printing Tips**

- For one-hit opacity through coarse meshes, use a coating procedure that builds a thick, even stencil to ensure a good column height of ink.
- For bleed resistance, use an underbase white such as 11835PFW Epic Quick White, 1117PFW Epic Polywhite, or 11195PFW Epic Athletic LB White.
- ▶ For cotton fabrics, underbase with 11335PFW Epic Sprint White.
- ▶ For cold-peel transfers, use a coated release paper.

# Compliance

#### ▶Non-phthalate.

▶ For individual compliance certifications, please visit www.wilflex.com/compliance.

# Precautions

- Perform fusion tests before production. Failure to cure ink properly may result in poor wash fastness, inferior adhesion and unacceptable durability. Ink gel and cure temperatures should be measured using a Thermoprobe placed directly in the wet ink film and verified on the production run substrate(s) and production equipment. It is the responsibility of the printer to determine that the correct ink has been selected for a specific substrate and the application processes meet your customer's standards or specifications.
- Avoid over flashing as it can result in poor intercoat adhesion of colors.
- ▶Avoid polyester fabrics where dye migration will occur.
- The viscosity of Epic Mixing Base is designed to enhance opacity and printability. Any alteration of viscosity should be minimized.
- Stir plastisols before printing.
- Do not dry clean, bleach or iron printed area.
- NON-CONTAMINATION OF EPIC INKS: Do not add or mix non-Epic inks, additives or extenders with Epic inks. All buckets, palette knives, stirring apparatus, squeegees, flood bars and screens must be cleaned properly and free of phthalates and pvc containing inks. Non-phthalate emulsions and pallet adhesives must be used. Failure to follow these precautions may cause phthalate contamination in violation of consumer protection laws and regulations.
- Any application not referred in this product information bulletin should be pre-tested or consultation sought with Wilflex Technical Services Department prior to printing.
- Email: techserviceswilflex@polyone.com



## Fabric Types



100% cotton, cotton blends, polyesters, some nylon (generally open weave or mesh types) as well as other synthetics



Mesh Counts: 86-305 t/in (34-120 t/cm) Tension: 25-35 n/cm<sup>2</sup>

## Squeegee



Durometer: 70/90/70 Edge: Square, Sharp Stroke: Medium for opacity. Fast for High Production. \*Do not use excess squeegee pressure.



## Non-Phthalate Stencil

Direct: 2 over 2 Capillary/Thick Film: N/A Off Contact: 1/16" (.2cm)



#### Flash & Cure Temperatures Flash: 160°F (70°C) Cure: 300°F (150°C)

# **Pigment Loading**

EQ: Use IMS System. MX: Use IMS System. PC: Use IMS System. \*All percentages listed at % by weight.



### **Epic Additives**

Extender: Epic Extender Base-20% max **Reducer:** Epic Viscosity Buster-3% max \*All percentages listed at % by weight.

## Storage



65-90°F (18-32°C) Avoid direct sunlight. Use within one year of receipt.



Clean Up Ink degradent or press wash.



**Health & Safety** MSDS: www.polvone.com or Contact your local CSR.

# 5000 PFB Epic Mixing Base: 05.2012V1

## PolyOne Wilflex™ inks by PolyOne.

www.wilflex.com/pib

#### GENERAL PURPOSE | BASE

©2013 PolyOne Corporation All Rights Reserved. Effective 5/05/2013. Not all Wilflex products are available in every country. The information in this publication is based on information and experience believed reliable. Since many factors may affect processing for an application, processors must carry out their own tests and experiments to confirm suitability for intended use. You must make your own determination of suitability for your intended use and environmental acceptability, the safety and health of your employees, and purchasers of your product.





