

require low cure temperatures.

Highlights

Printing Tips

that the ink film reaches 290°F (145°C).

Compliance

Precautions

Stir plastisols before printing.

Do not dry clean, bleach or iron printed area.

▶Email: techserviceswilflex@polyone.com

▶Non-phthalate.

procedures outlined in the Wilflex User's Manual.

Low cure properties.

►Matte finish. Low tack surface. Excellent printability.

17600LBFF Epic Top Score LBFF Base

Delivers high stretch and bleed resistance in one package.

Wilflex™ Epic Top Score Base is a non-phthalate plastisol ink designed to meet the changing

demands of the athletic market by delivering a solution for printing on polyester substrates that

▶For optimal bleed resistance, print Epic PolyWhite or Top Score White as underbase. Set the dryer belt at the

highest possible speed while still ensuring that the ink film reaches 300°F (150°C). For optimal stretch, print

Epic Performance White as underbase. Set the dryer belt at the highest possible speed while still ensuring

▶Polyester fabrics are likely to have dye migration issues and may require use of additional bleed blocker, such

as Épic Performance Underbase Gray. To determine a material's bleed potential, please reference the testing

Perform fusion tests before production. Failure to cure ink properly may result in poor wash fastness, inferior adhesion and unacceptable durability. Ink gel and cure temperatures should be measured using a Thermoprobe placed directly in the wet ink film and verified on the production run substrate(s) and production equipment. It

Some fabric dyes may cause ghosting effect if not properly tested. Pre-test on light colored or stone washed garments. Avoid stacking printed garments while hot because such colors are more prone to color distortion (ghosting). Fabric and dye characteristics can vary between manufacturers and dye lot.

▶NON-CONTAMINATION OF EPIC INKS: Do not add or mix non-Epic inks, additives or extenders with Epic inks.

Any application not referred in this product information bulletin should be pre-tested or consultation sought

All buckets, palette knives, stirring apparatus, squeegees, flood bars and screens must be cleaned properly and free of phthalates and pvc containing inks. Non-phthalate emulsions and pallet adhesives must be used. Failure to follow these precautions may cause phthalate contamination in violation of consumer protection laws and

is the responsibility of the printer to determine that the correct ink has been selected for a specific substrate and

▶ Building a thick ink deposit on the polyester substrate provides additional bleed blocking power. To accomplish this, use the following coating screen method with a wet-on-wet application: 1) Coat print side; 2) Coat squeegee side; 3) Coat print side; 4) Coat squeegee side. Always end coating on the squeegee side to push

If printing on a hard metal surface, use a palette covering to allow for a softer printing surface.

the emulsion to the print side. Dry screens with print side facing the floor.

▶ For individual compliance certifications, please visit www.wilflex.com/compliance.

the application processes meet your customer's standards or specifications.

Avoid over-flashing as it can result in poor intercoat adhesion of colors.

with Wilflex Technical Services Department prior to printing.

Product Information Bulletin

Recommended Parameters



Fabric Types

100% polyester, polyester blends, 100% nylon Jersey



Mesh

Counts: 86-158 t/in (34-62 t/cm) Tension: 25-35 n/cm²



Squeegee

Durometer: 60-70 Edge: Square, Sharp

Stroke: Hard flood, Slow-Medium

stroke

*Do not use excess squeegee pressure.



Non-Phthalate Stencil

Direct: 2 over: Capillary/Thick Film: 30+ micron

Off Contact: 1/16" (.2cm)



Flash & Cure Temperatures

Flash: 160°F (70°C) Cure: 290°F (140°C)



Pigment Loading

EQ: 35% max MX: N/A PC: 15% max

*All percentages listed at % by weight.



Epic Additives

Extender: N/A

Reducer: Epic Viscosity Buster-1% max *All percentages listed at % by weight.



Storage

65-90°F (18-32°C) Avoid direct sunlight. Use within one year of receipt.



Clean Up

Ink degradent or press wash.



Health & Safety

MSDS: www.polvone.com or Contact your local CSR.

EPIC TOP SCORE LBFF BASE : 07.16.2013 v1

7600LBFF



www.wilflex.com/pib

ATHLETIC | BASE

©2013 PolyOne Corporation All Rights Reserved. Effective 5/05/2013. Not all Wilflex products are available in every country. The information in this publication is based on information and experience believed reliable. Since many factors may affect processing for an application, processors must carry out their own tests and experiments to confirm suitability for intended use. You must make your own determination of suitability for your intended use and environmental acceptability, the safety and health of your employees, and purchasers of your product.

888-578-5713